Monsanto INDUSTRIAL CHEMICALS CO.

FROM (NAME & LOCATION) E. E. Cowell, S. Second St., St. Louis

DATE : May 8, 1972

SUBJECT : VINYL ASBESTOS TILE

REFERENCE :

cc: W. W. Touchette, Res. 3
J. R. Darby, Res. 1
M. W. Farrar, R2E
P. R. Graham, PGRAH

TO : E. S. Tucker
Res. 2

Vinyl asbestos tiles have been given to Bill Mees for your environmental studies.

There are 9 tiles, size 7 x 10", of 4 different plasticizers. Tiles are of 0.087" thickness and have a McBurney Hardness of 7 ± 0.5. The following are the complete formulations.

Borden's VC 113F	100	97	100	96
DOP	39			
S-160		42		
DHP (Enjay)			39	
C_{7-9} Benzyl Phthalate				43
DICy	4	4	4	4
TiO_2	20	20	20	20
Coalinga Asbestos	92	92	92	92
Limestone (40 mesh)	367	367	367	367

A sample of each ingredient was also given to Bill Mees.

E. E. Cowell

rz

E. E. Cowell

DSW 587891

STLCOPCB4093227