

The RUBEROID Co.

Mr. W. Gebhard

Feb. 15, 1965

Messrs. Hughes & Schwingen
Miss B. Brangenberg

FILTER PRESS FORMULAE

Two recent formula changes have been made and for the record the designation and percentages are as follows:

1. FP 61

	<u>%</u>	<u>Lbs/mix</u>
Dicalite	48.073	923
Lime	32.031	615
W3	9.375	180
SR	4.271	82
Sodium Silicate (SS20)	2.083 ¹ / ₃	40
Amorphous silica (Tripoli)	2.083 ¹ / ₃	40
Chromite	2.083 ¹ / ₃	40
Total - - - - -	100.000	1920 lbs.

2. FP 62

Dicalite	49.096	923
Lime	32.713	615
W3	9.574	180
SR	4.362	82
Sod. Silicate (SS20)	2.127 ¹ / ₂	40
Chromite	2.127 ¹ / ₂	40
Total - - - - -	100.000	1880 lbs.

AD/gw

A. DIGENNI

MICH01054

01-0201825