

BFGoodrich

J. C. McCool

Akron, D/0020, B/5-H

DATE YOUR LETTER

O. S. Kurtz

Brecksville R & D Center, D/8506

DATE THIS LETTER

Feb. 23, 1976

25-1612

Your sample of a yellow crystalline material submitted to us for identification and lead content was given log #48. The material was identified by IR as 2,5-di-tert-amyl-quinone. We found 18.5 μ g of Pb in 128 mg of material by AA. This crystalline material did not completely dissolve so this % Pb may be on the low side.

O. Sue Kurtz
O. Sue Kurtz

jb

cc: P. M. Zakriski
R & D Files

THE B. F. GOODRICH COMPANY

RESEARCH & DEVELOPMENT

AKRON, OHIO 44316

TELEPHONE (216) 382-1000

BFG-I- 452