MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE N-7888-A LOT 88206

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
191	15	176		
219	15	204		
212	15	197		
214	15	199		
205	15	190		
	STUMP			

TOTAL NET WT. 966 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

1-24

MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE A-7888-A LOT 88206

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
191	15	176		
219	15	204		
212	15	197		
214	15	199		
205	15	190		
	STUMP			

TOTAL NET WT. 966 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

1-24-1

DUP050292124

MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE D-7888-A LOT 88206

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
207	15	192		
207	15	192		
216	15	201		
170	15	155		
61	15	46		
	STUMP			

TOTAL NET WT. 786 PKG. N–CODE

PROD. SPVR. DATE 1-24 WHSE. OPER.

DUP050292125

N 31802.01

MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE D-7888-A LOT 88206

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
207	15	192		
207	15	192		
216	15	201		
170	15	155		
61	15	46		
	STUMP			

TOTAL NET WT. 786 PKG. N–CODE

PROD. SPVR. DATE 1-24 WHSE. OPER.

DUP050292126

CG 88 CODE SF-88 PKG. ____

→

EST. WGT. ~~[illegible]~~ 1714 LBS.

Processing: Call Waste Treatment before starting to fill press

Note: STUMPPRESS AT 40 CAKES

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(E) SF-88	BBK 9-28-77
	DCG 10-3-77
TYPED BY	
NSA 10-7-77	

MAKING NOTES

REMARKS

NAME: QAQ

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT		181			
DATE		12-22 Sl.			
TIME		1230			
RELEASED BY		[illegible]			
PRESS	~~[illegible]~~	39			
NO. OF CAKES	~~[illegible]~~	40			

PRESS without AGITATION

WASH TO 2500 OHMS with 90-100°F water

TEST AFTER 12 HOURS

LOAD on 6 cars

ROPE OFF NECESSARY AREAS PRIOR TO FILLING PER PROCEDURE No P0050

SAMPLES 1-16 oz jar

DELIVER TO Anal Lab

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	1150				
CAKES USED	40				
HOURS TO FILL	12				
WATER ON	23				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 220°F

LOCK LIDS - either new L/P or painted out with liners

SAMPLES 1-16 oz jar

DELIVER TO Anal Lab

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 10

NO. CARS PULLED LUMP WGT. 1754

SAMPLED BY RELEASED BY

-GRINDING-

MILL #1 LSP 1/8"RP SCREEN 1750 RPM

MAX. TEMP. 150 °F

PACK in same L/P & LOCK LIDS. Stencil top & sides: N-7888-A Lot, Gross, Tare, Net Wgt

Deliver material with card & 1 pt coshipment sample to RM Supervisor

RM: Hold until given OK by PE to ship to Nwpt.

SAMPLE AFTER MIXING

SAMPLES 1 Env. and 1 pt can

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED 1/23/81

SAMPLED BY #177 RELEASED BY

DUP050292127

N 31802.02

39/8

CG 88 CODE SF-88 PKG. ____

DEC 22 88206

EST. WGT. ~~2000~~ 1714 LBS.

Processing: Call Waste Treatment before starting to fill press

PROCESSING INS[redacted]ATCH UNIT

MFS
DRS on Floor

PROCE[redacted]	APPROVED BY
(E) SF-88	BBK 9-28-77
	DCG 10-3-77
TYPED BY	
NSA 10-7-77	

MAKING NOTES

REMARKS

NAME: QAQ

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						HOURS TO FILL					
PRESS	38	39				WATER ON					
NO. OF CAKES	60	60				OHMS					
PRESS without		AGITATION				HRS. WASHED					
WASH TO 2500		OHMS with 90-100°F water				OHMS					
TEST AFTER 12		HOURS				HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES 1-16 oz jar

DELIVER TO Anal Lab

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 220°F

LOCK LIDS - either new L/P or painted out with liners

LUMP: - OK - WET - SALTS - CONTAMINATED

DRYER SECTIONS USED:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS

SAMPLES 1-16 oz jar

DELIVER TO Anal Lab

NO. CARS PULLED LUMP WGT.

SAMPLED BY RELEASED BY

-GRINDING-

MILL #1 LSP 1/8"RP SCREEN 1750 RPM

MAX. TEMP. 150 °F

PACK in same L/P & LOCK LIDS. Stencil top & sides: N-7888-A Lot, Gross, Tare, Net Wgt

Deliver material with card & 1 pt coshipment sample to RM Supervisor

RM: Hold until given OK by PE to ship to Nwpt.

SAMPLE AFTER / MIXING

SAMPLES 1 Env. and 1 pt can

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050292128

N 31802.03

88206
51
16 0.00 *

1.78 +
0.14 -
2.15 +
0.14 -
1.99 +
0.14 -
1.93 +
0.14 -
2.11 +
0.14 -
1.97 +
0.14 -
1.98 +
0.14 -
1.68 +
0.14 -
1.75 +
0.14 -
1.60 +
0.14 -
17.54 *

DUP050292129

N 31802.04