A & L PRINTERS, NEWARK, N.J.

MD-2-A

PACKAGE TICKET

(PRESSCAKE ONLY)

CODE 4C-5-A LOT 33986

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
360#	22		335-D5	
300#	1			

TOTAL NET WT. 8,220# D.C. _____ %

PKG. N–CODE _____

PROD. SPVR.	PROD. OPER.	DATE	WHSE. OPER.
[illegible]	#82/#12	1/24/80	

36/105

CG 46 CODE YC-5-A PKG. ____

→

EST. WGT. JA 33986 2450 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
(C) YC-5-A	EWK 9/23/76
	DCG 10/ 6/76
TYPED BY	
NE.3/7/77	

MAKING NOTES

REMARKS

NAME: "DALAMAR" YELLOW

BLEEDING

-PRESSING-

INSTRUCTIONS					RECORD					
VAT				105	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				1-23	STARTED	230Pm				
TIME				200P	CAKES USED	66				
RELEASED BY				VDC	WATER ON	7Pm				
PRESS	32	33	35	56	HRS. WASHED	3½				
NO. OF CAKES	60	62	60	66	OHMS	4000				
PRESS with out		AGITATION			HRS. WASHED					
WASH TO 4000		OHMS with 35-75°F water			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD In metal drums at 360# net/Dr.					OHMS					
					CAKE CONDITION					
					NO CARS LOADED					
Air blow presscake for					EXPLAIN LOSSES					
15 min at 40 PSI										
THIEF SAMPLE PERSON										
SAMPLES ~~1-8 oz JAR~~ + 1 qt										
DELIVER TO ctl for color					SAMPLED BY		RELEASED BY			

-DRYING-

HOURS	L.V.	H.V.	LUMP: - OK - WET - SALTS - CONTAMINATED
TEMP.	°F	°F	
DO NOT DRY			
			ADDITIONAL DRYING HOURS REQUIRED
SAMPLES			NO. CARS PULLED LUMP WGT.
DELIVER TO			SAMPLED BY RELEASED BY

-GRINDING-

MILL	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
			EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING			DATE MIXED	
SAMPLES				
DELIVER TO C T L			SAMPLED BY	RELEASED BY

DUP050293339

N33115.01