

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY 907 LOT 37489

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>1486</u>	<u>1</u>	<u>T-102</u>		
-------------	----------	--------------	--	--

<u>1980</u>	<u>1</u>	<u>T-116</u>		
-------------	----------	--------------	--	--

--	--	--	--	--

--	--	--	--	--

--	--	--	--	--

STUMP Lump-3,440

TOTAL NET WT. 3456 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

JT 101 3050

N34966

CG 03 CODE KY-907-D PKG.

OCT-17 80 37489

EST. WGT. 1853 LBS.

*012
H*

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-907-D (F)	FWK 12/12/
Alternate	DCG 12/14/
TYPED BY	
ri 2/8/77	
MAKING NOTES	

REMARKS

TOTAL WGT. ~~6053~~ 3480

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS				- PRESSING -		RECORD				
AT	362					PRESSLOAD	1ST	2ND	3RD	4TH
ATE	10-20-80					STARTED	1:00 PM			
IME	10: PM					CAKES USED	72			
RELEASED BY	S. B.					WATER ON	7 PM			
RESS	96	95				HRS. WASHED	4			
O. OF CAKES	72	72				OHMS	8500			
RESS With	AGITATION					HRS. WASHED				
ASH TO	2000	OHMS with 135-145°F water				OHMS				
EST AFTER	3	HOURS				HRS. WASHED				
OAD	on 10 cars					OHMS				
						CAKE CONDITION	5			
						NO. CARS LOADED				
						EXPLAIN LOSSES				

AMPLES 8oz Jar
DELIVER TO CTL for color

BLH

SAMPLED BY 499 RELEASED BY 125

- DRYING -

RY	24	HOURS AT	180 °F	LUMP: - OK - WET - SALTS - CONTAMINA
Dry on first stage only.				
Re-set every 5 hours til dry.				
				ADDITIONAL DRYING HOURS REQUIRED
				NO. DRUMS 12
AMPLES				NO CARS PULLED
LIVER TO				LUMP WGT. 3440
				RELEASED BY D.C.

- GRINDING -

ILL 939 HSP 1/8" RP	SCREEN 3500	RPM	SCREEN	RPM
MAX TEMP.	170 °F		MAX. TEMP.	° F
			EXPLAIN LOSSES	
AMPLE / WITHOUT MIXING			DATE MIXED	
AMPLES 1 ENV & 1PT CAN				
LIVER TO CTL			RELEASED BY	

0.00 *

37489
41
188

19.79 +
3.12 +
0.12 -
3.00 +

0.12 -
2.94 +
0.12 -
3.03 +
0.12 -
3.12 +
0.12 -

34.40 *
* 34.40M+

12
DRUMS

95
262
CG 03 CODE KY-907-D PKG.
→ OCT-17 80 37489
EST. WGT. 1853 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-907-D (F)	FWK 12/12/
Alternate	DCG 12/14/
TYPED BY	
ri 2/8/77	
MAKING NOTES	

REMARKS

TOTAL WGT. ~~6053~~

3480

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT	262					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE	10-20-80					STARTED	1:00 PM				
IME	10: PM					CAKES USED	22				
RELEASED BY	S. B.					WATER ON	7 PM				
RESS	96	95				HRS. WASHED	4				
O. OF CAKES	72	72				OHMS	2500				
RESS With						HRS. WASHED					
ASH TO	2000					OHMS					
EST AFTER	3					HRS. WASHED					
OAD on	10 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED					
						EXPLAIN LOSSES					

AMPLES 802 Jar
ELIVER TO CTL for color

SAMPLED BY 499 RELEASED BY 105

-DRYING-

RY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINA

Dry on first stage only.

Re-set every 5 hours til dry.

ADDITIONAL DRYING HOURS REQUIRED

AMPLES
ELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 12
LUMP WGT. 3440
RELEASED BY D.C.

-GRINDING-

ILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX TEMP. 170°FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE / WITHOUT MIXING
AMPLES 1 ENV & 1PT CAN
ELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY