VISCOSITY WORK SHEET

Item 5498-99	P.T. No.	Date 4/18/56
Worker Stanley	Polymer Lucite	Solvent Chlorobenzene
For Wolfe	Charge 1333	Temperature 20° C
Viscometer No. III	Efflux Time 152.0; 152.0	Weight: Gross 3.6053
Viscometer No. 8	Efflux Time 159.5; 159.4	Tare 3.4803
Viscometer No. A	Efflux Time 169.9; 170.0	Net 0.1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.
5108-56-C	557	8	201.2; 201.2	1.262	0.47 ✓
5108-56-D	M1L	A	216.5; 216.8; 216.7	1.276	0.49 ✓

PC-1

4/19/56 MAY

N38927