CODE 40-010-B LOT E-1209

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
50	111			
	STUMP			

TOTAL NET WT. _____ PKG. N–CODE _____

PROD. SPVR. DATE WHSE. OPER.

_____ 9/1/17 _____

ATTACHMENT I

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YC-010-B PKG ____

LOT MAY -0-81-E1047

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

NON-BLEEDING

PROCESSES APPROVED BY

YC-010-B (G) F.POST 4/14/81

ALTERNATE

TYPED BY JMH

MAKING NOTES

JOB NAME: 01YC010BPG

INSTRUCTIONS			= PRESSING =	RECORD				
				1ST	2ND	3RD	4TH	5TH
VAT	245		PRESSLOAD	350				
DATE	4-23		STARTED	5PM				
TIME	1630		CAKES USED					
RELEASED BY			WATER ON					
PRESS	2	92	HRS. WASHED					
NO.OF CAKES	54	54	OHMS					
PRESS WITH AGITATION			HRS. WASHED					
WASH TO 2000 OHMS WITH 35-75 F WATER			OHMS					
TEST AFTER 2 HOURS			HRS. WASHED					
LOAD ON 7 CARS			OHMS					
			CAKE CONDITION					
			NO CARS LOADED	6				
			EXPLAIN LOSSES					
SAMPLES			SAMPLED BY					
DELIVER TO			RELEASED BY					

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F

(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD'

No record of any previous losses recorded.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO CARS PULLED 6

SAMPLED BY

RELEASED BY RH

NO DRUMS 18

LUMP WGT 5545

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM

MAX. TEMP DEG F

SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SAMPLE WITHOUT MIXING

SAMPLES

DELIVER TO CTL

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050095846

1047
41
365

3.25 +
0.12 -
3.15 +
0.12 -
3.48 +
0.12 -
3.41 +
0.12 -
3.08 +
0.12 -
3.45 +
0.12 -
3.18 +
0.12 -
3.02 +
0.12 -
3.11 +
0.12 -
3.26 +
0.12 -
3.36 +
0.12 -
3.25 +
0.12 -
3.13 +
0.12 -
3.47 +
0.12 -
3.25 +
0.12 -
3.05 +
0.12 -
2.85 +
0.12 -
2.86 +
0.12 -
55.45 *

DUP050095847