

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE BT428 DOT 37235

NET WT/PKG NO. PKG PACK WGT LOCATION PQ

20 3026 56

TOTAL NET WT. 3026 PKG. N-CODE

PROD. SPUR DATE 10/71 WHSE. OPER. 292

~~BT428~~ BT428 2900

O.T

147.+
142.+
139.+
144.+
158.+
141.+
175.+
155.+
153.+
152.+
137.+
148.+
174.+
150.+
138.+
171.+
145.+
151.+
157.+
149.+
3026.T

96
901

CO 32 CODE RT-428-D PKG
SEP 30 1980 37200
EST. WOT. 3066 LBS.

PROCESSING INSTRUCTIONS BATCH UNIT

PROCESSED BY
RT-428-D (V) JIG 12-10-78
DCG 08-10-78

TYPED BY
GIMW081878
MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT 901
DATE 9-29-80
TIME 1:20 PM
RELEASED BY
PRESS 95
NO. OF CAKES 76
PRESS with AGITATION
WASH TO 3000 OHMS with 35-75°F water
TEST AFTER 3 HOURS
LOAD on 10 cars
1. Press Immediately Code
2. Instruct Making Area to add 10# N-588-A halfway thru pressing
3. Clean magnetic separator after pressing
Cleaned by 375 Time cleaned 9 AM

PRESSLOAD STARTED 1ST 2ND 3RD 4TH 5TH
CAKES USED 88
WATER ON 9
HRS. WASHED 3000
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO. CARS LOADED 11
EXPLAIN LOSSES
Color washing on floor from
deck plate 298
Informal Supervisor

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

-DRYING-

DRY 20 HOURS AT 220 °F
Hold on track 30 min before dumping

LUMP: OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 18
LUMP WGT. 12900
RELEASED BY

-GRINDING-

MILL 2 HSP 1/8" RP SCREEN 3350 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 Env
DELIVER TO CTL

DATE MIXED
SAMPLED BY 10-7-80
RELEASED BY

0.00 *
0.00M+
1.98 +
0.14 -
1.90 +
0.14 -
1.93 +
0.14 -
1.75 +
0.14 -
1.87 +
0.14 -
1.96 +
0.14 -
1.93 +
0.14 -
1.91 +
0.14 -
1.89 +
0.14 -
1.84 +
0.14 -
1.89 +
1.44 -
1.91 +
0.14 -
1.93 +
0.14 -
1.89 +
0.14 -
1.80 +
0.14 -
1.76 +
0.14 -
1.72 +
0.14 -
0.91 +
0.14 -
29.00
29.00M