

HARDNESS 90+/-5

STOCK NO. 06012

GOODYEAR BLK. 2A

COMPOUNDED BY

01/19/88

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH	
159	OXY 200	47.75 C	34.35	39.80	95.50	A
90447	DYPHOS XL	5.00	1.11	4.16	10.00	A
165	VANSTAY 5515ND	1.00	.72	.83	2.00	A
166	FIRESHIELD H	3.00	.58	2.50	6.00	A
167	SANTOVAR A	.20	.19	.16	.40	A
90115	WINGSTAY 100	.50	.38	.41	1.00	A
168	ACRYLORD K120	5.00	5.15	4.16	10.00	A
169	KENAMIDE E	.50	.52	.41	1.00	A
156	CHEMIGUM NBR-P83	27.25 C	27.53	22.71	54.50	A
158	CHEMIGUM NBR P-612-A	27.25	27.53	22.71	54.50	A
105	VCP4797 90VCP 01 BLACK	2.00	1.54	1.66	4.00	A
90122	FLECTOL H	.50	.47	.41	1.00	A

TOTAL COST
109.42

~~TOTAL COST~~
~~103.56~~

TOTAL	119.95	100.07	99.99	239.90
1.21	PHYSICAL PROPERTIES			
USE	-	SPEC.	MIN.	MAX.
REPLACES	-	SPECIFIC GR.	1.199	
REASON	-	HARDNESS		
COLOR	-	TENSILE		
REQUIRMENTS TO MEET	-	ELONGATION		
	-	MODULUS @		
	-	MOONEY @		
	-	SCORCH		
	-	CURE		
	STOCK CONTROL TEST			
LAB	-			
COST	-			
MIXING	-			

CHARDO 01357