

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KF 787 LOT AAK 73

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>1720</u>	<u>1</u>	<u>T</u>	<u>40</u>	
<u>1720</u>	<u>1</u>	<u>T</u>	<u>77</u>	

STUMP Ump 3460

TOTAL NET WT. 3440 PKG. N-CODE _____

PROD. SPVR. NA DATE 2 14 82 WHSE. OPER. _____

DATE PRINTED: 1/06/82

NON-BLEEDING

PROCESSES: APPROVED BY
KY-787-D (R,T) FWP 11/05/81

TYPED BY JMH

EST. WT. 3394* LBS.

MAKING NOTES

JOB NAME: 03KY787DPT

INSTRUCTIONS

= PRESSING =

RECORD

VAT						240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						1/18/82				STARTED					
TIME						8:15 AM				CAKES USED					
RELEASED BY						CAC				WATER ON					
PRESS	22	23	95/96	24	25					HRS. WASHED					
NO. OF CAKES	46	46	40	52	48					M MHOS					
PRESS WITH AGITATION										HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER										M MHOS					
TEST AFTER 2 HOURS										HRS. WASHED					
LOAD ON 6 CARS										M MHOS					
										CAKE CONDITION					
										NO CARS LOADED					
										EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 12 HOURS AT 220* F
THEN DRY 8 HRS AT 160* F

LUMP: - OK - WET - SALTS + CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 13
LUMP WGT 3460

= GRINDING =

MILL 939HXP 3/32" RP SCREEN 3500 RPM
MAX. TEMP 150 DEG F

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CIL :

DATE MIXED

SAMPLED BY
RELEASED BY

73
41
130
0
279
12
230
12
236
12
275
12
233
12
275
12
230
12
332
14
250
12
237
12
233
12
231
12
155
12
240