

CODE YE-698-D PKG

LOT MAY -0-81-E1442

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
	12/2/81	1:55 PM	OK		54																	

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

RPM SCREEN
MAX. TEMP. RPM
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1442
4100
18

0.00 *
3.73 +
0.14 -
3.49 +
0.14 -
3.66 +
0.14 -
3.75 +
0.14 -
3.37 +
0.14 -
3.47 +
0.14 -
2.18 +
0.14 -
22.67 *

1442
4100
18

0.00 *
22.67 +
3.58 +
0.14 -
3.63 +
0.14 -
3.49 +
0.14 -
3.68 +
0.14 -
3.62 +
0.14 -
3.47 +
0.14 -
3.52 +
0.14 -
3.10 +
0.14 -
2.31 +
0.14 -
51.81 *