

Foseco®

PROFAX® 31

TYPICAL ANALYSIS

|                                |               |
|--------------------------------|---------------|
| SiO <sub>2</sub>               | 85.73%        |
| L.O.I. (Organics)              | 5.58%         |
| CaO                            | 3.50%         |
| MgO                            | 1.78%         |
| Al <sub>2</sub> O <sub>3</sub> | 1.70%         |
| FeO                            | 1.20%         |
| Moisture                       | 0.24%         |
| Fe <sub>2</sub> O <sub>3</sub> | 0.15%         |
| MnO                            | 0.02%         |
| K <sub>2</sub> C               | 0.01%         |
| Other Oxides                   | 0.01%         |
|                                | <u>99.92%</u> |

Before use, the board contains less than 4% asbestos fiber. After heating to 2000° F the residual fiber content will be below 2%.

8/2/72  
kms

FOS-00-0000003962

FOSECO 2019