

FORMULA RECORD			
Exp. No.	Date	Class	Rev. No.
	5-27-41		A1445
Name	Canvas Preservative Buff		Card No. 3 See No.
39 LBS.	412 or 412E	Customer	Marine Trade
38 "	2506	To Match	Standard
25 "	306		
25 "	2500	Weight Per Gal.	17.95 Visa 15" 75 deg. #2 cup
10 "	(2846)C	Baume	Std. of Fineness 2P No Label Required
27 "	(3241)K	Lbs. Gals. per hour	Mill
7 "	(629)	New Std. Sample Required	No Date Rec'd
4 "	(2)	Reason for Revision	Replace 108N with 412
170 "	Paste Wt		
220 "	(2956)R		
426 "	(348)		
"		Normal Output	100
"		Est. Mfg. Loss	3%
"		Department	Supt.
"		Label Analysis Checked-Date	
"		Approved	DFH
"		Formulator	D. J. H. 1.1.1

A 135 9-40 5-79

N16353

0007 SMD 00007

MANUFACTURING INSTRUCTIONS:			
Reduction: Amount Application: Surface Curves Reducer Used Method Brush			
No. Coats Drying Time: Touch 1 hr Handle Recast 18 hrs Stencil Wrap Sand Rub			
Baking Time and Temp Gloss Film Special Tests			
FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND			
NEWARK			
KENSINGTON			
OAKLAND			
DALLAS			
LOS ANGELES			
MONTREAL			
COST DEPT.			
FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
ALLIED RESEARCH			
GIBBSBORO			
DAYTON			
DETROIT			
LONDON			
AUSTRALIA			
M-S			
CHL. TECH. SERV.			
DATE	SLIP No.	AMOUNT	
PRODUCTION			

0007-SWP-063072