CE 01 CODE YE-698-D PKG ____

LOT MAY -0-81-E1450 01

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE — —
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

## INSTRUCTIONS = PRESSING = RECORD

| | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| VAT | | | | PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
| DATE | | | | STARTED | | | | | |
| TIME | | | | CAKES USED | | | | | |
| RELEASED BY | | | | WATER ON | | | | | |
| PRESS | 2 | 92 | | HRS. WASHED | 4 | | | | |
| NO.OF CAKES | 54 | 54 | 54 | OHMS | 5 | | | | |
| PRESS WITH AGITATION | | | | HRS. WASHED | 4000 | | | | |
| WASH TO 2000 OHMS WITH 35-75 F WATER | | | | OHMS | | | | | |
| TEST AFTER 2 HOURS | | | | HRS. WASHED | | | | | |
| LOAD ON 7 CARS | | | | OHMS | | | | | |
| | | | | CAKE CONDITION | | | | | |
| | | | | NO CARS LOADED | 7 | | | | |
| | | | | EXPLAIN LOSSES | | | | | |

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

## = DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 19
LUMP WGT 5630

## = GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

698
1450
41
56

0.00 *

3.17 +
0.12 -
2.98 +
0.12 -
3.26 +
0.12 -
0.12 -
3.36 +
3.39 +
0.12 -
3.27 +
0.12 -
3.26 +
0.12 -
3.30 +
0.12 -
3.46 +
0.12 -
3.24 +
0.12 -
3.43 +
0.12 -
3.42 +
0.12 -
3.23 +
0.12 -
3.27 +
0.12 -
1.31 +
0.12 -
45.55 *

15

1450
41
305

0.00 *

4

3.14 +
0.14 -
3.36 +
0.14 -
3.23 +
0.14 -
1.56 +
0.14 -
10.73 *
4555
5630

DUP050095897