MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE SP501 LOT 3C711

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	1	54	11	
	STUMP	hemp	60	

TOTAL NET WT. 54 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
	8-9-1	160

N37486

CG 18 CODE GP-501-D PKG. ____

→JUL·30·80 36711

EST. WGT. 0 [redacted] LBS.

SPLIT OFF: 60# FROM GP-501-D LOT 35408
FOUND IN PROCESSING AREA

(1)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
GP-501-D (P)	EWK 03-17-75
	DCG 03-17-75
TYPED BY	
emw062979	

MAKING NOTES

REMARKS

NAME: RAMAPO® GREEN B

NON-BLEEDING

INSTRUCTIONS — PRESSING — RECORD

VAT					
DATE					
TIME					
RELEASED BY					
PRESS	12	20	21	26	
NO. OF CAKES	3 x 36	2 x 42	2 x 42	3 x 40	

PRESS with AGITATION
WASH TO 4000 OHMS with 35-75°F water
TEST AFTER 3 HOURS
LOAD on 8 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED					
CAKES USED					
WATER ON					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

Dry 12 hrs at 180°F
Dry 12 hrs at 140°F

Std & Abrev Dry P & S
Sides 180 DN
Cool - 100
Use 41 Gal L/P

LUMP: - OK - WET - SALTS - CONTAMINATED
Dryer sections used:

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 1

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 60
SAMPLED BY RELEASED BY BLH

-GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM
MAX. TEMP. °F
Use 41 Gal L/P

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES


SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 2 Pt Cans
DELIVER TO CTL

DATE MIXED

SAMPLED BY TJH 8/6/80 RELEASED BY

DUP050042183

N37486.01



DUP050042184