PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG ____

LOT G2H43 JUN 28 1982

EST. WT. 5527* LBS.

OK/AP

NON-BLEEDING 6/22/82

92/242

PROCESSES APPROVED BY
YE-698-D (S) F.POST 06/22/82
ALTERNATE
TYPED BY JMH

MAKING NOTES _____

JOB NAME: 01YE698DPS

INSTRUCTIONS EC = PRESSING = RECORD

VAT			242		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			6-30-82		STARTED	930PM				
TIME			3:20A		CAKES USED	54				
RELEASED BY					WATER ON	1PM				
PRESS	2	92	93		HRS. WASHED	2 1/2				
NO.OF CAKES	54	54	54		M MHOS	130				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER					M MHOS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 7 CARS					M MHOS					
					CAKE CONDITION					
					NO CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY
RELEASED BY A.K

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE

DELIVER

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 18
LUMP WGT 5475

CO-GRIND PER CTL INSTRUCTIONS GRINDING
MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE
SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N32784

DUP050464294

41

43

267

330
12
330
12
323
12
335
12
318
12
325
12
329
12
320
12
319
12
321
12
323
12
326
12
320
12
292
12
363
12
322
12
317
12
178
12
5475

N32784.01

DUP050464295