

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 15788 LOT 38031

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

1.794 1 T-2521.684 1 T-152STUMP LUMP 3.581TOTAL NET WT. 3.478 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

JU 1214140

N34823

22
244

CO 03 CODE KY-788-D PKG.
→ NOV 15 80 38031
EST. WGT. 960 LBS.

OK
TA

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSED KY-788-D (J)	APPROVED BY EWK 9/22/77
	DCG 9/27/77
TYPED BY NE 2/17/77	
MAKING NOTES	

REMARKS

Total Wgt. 3560# Req()

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

ST	1ST	2ND	3RD	4TH	5TH
DATE	244				
TIME	11/16/80				
RELEASED BY	344				
WASH	22	23	24		
G. OF CAKES	46	46	46		
WASH WITH	AGITATION				
WASH TO 2000	OHMS with 35-75°F water				
TEST AFTER 2	HOURS				
LOAD on 6 cars					
PRESS LOAD	1ST	2ND	3RD	4TH	5TH
STARTED	5 AM				
CAKES USED	46				
WATER ON	2.45 PM				
HRS. WASHED	2 1/2				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				
EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO Ctl for Color

SAMPLED BY 4747 RELEASED BY 14

-DRYING-

Dry 12 hrs at 220 °F
Then Dry 8 hrs at 160 °F

LUMP: -- OK -- WET -- SALTS -- CONTAMINA

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED 6
SAMPLED BY

No Drums 14
LUMP WGT. 3581
RELEASED BY 00.

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE 1 / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

38001

41

16

0

282

12.

280

12.

274

12.

272

12.

271

12.

275

12.

273

12.

283

12.

271

12.

286

12.

275

12.

288

12.

284

12.

170

12.

3501

14
pieces