

Thinning Recommendations for Zilo Heavy Paste

NEW WORK	First Coat	Second Coat	Third Coat
Salt Wood	100 Lbs.	100 Lbs.	100 Lbs.
ZILO	4 Gals.	2 Gals.	3 1/2 Gals.
Pure Raw Linsed Oil	2 Gals.	2 Gals.	1 Pint
Pure Tur- pentine	1 Pint	1 Pint	1 Pint
Drier	7 1/4 Gals.	7 1/4 Gals.	7 1/4 Gals.

"If boiled Linsed Oil is used omit Drier.

REDUCING TABLE

FOR 12 1/2, 25, AND 50-POUND PACKAGES

50-LB. KEGS—Divide the above quantities by 2.

25-LB. KEGS—Divide the above quantities by 4.

12 1/2-LB. KEGS—Divide the above quantities by 8.

IMPORTANT NOTE — Do not spoil the high quality of this Zilo by mixing it with cheap oil and cheap drier. USE THE BEST.

Add the oil a little at a time and stir in each portion thoroughly.

RESINOUS WOOD — Reduce as directed above except the first coat should have larger percentage of Pure Turpentine.

PREVIOUSLY PAINTED SURFACES — When in good condition, reduce as directed above for second and third coats.

UNPAINTED OLD WEATHERED LUMBER — Reduce as directed above except first coat should have larger percentage of Pure Raw Linsed Oil.

Since conditions and surfaces vary, no definite amount can be given.

FLAT FINISH — For flat finish on interior walls and woodwork, mix the contents of 100 pound pail with two gallons of Flating Oil for both coats.

CAUTION — Allow each coat to dry. In all painting, give plenty of time for each coat to dry before applying another. Inside work should have at least twenty-four hours and outside work two or three days between coats.

HERE'S WHAT YOU, TOO, WILL THINK OF ZILO

Gentlemen: The fact that we are spreading approx-
imately 5000 gallons of paint a year along the New Jersey
coast has led me to believe that we are satisfying our
customers.

You know credit for our success is not only due to the
quality of the paint but also to the service we give. We
the painter's spray coat, but in the material used as
well. Therefore I am taking it upon myself to pass the
word on to my brothers in trade, "The Master Painter,"
who may wish to overcome the many girls experienced
in exterior painting at the moment.

ZILO is the material we have used for over five years.
We are very sure the position it holds is not superior, and I
am sure it is the best material I have used and that
there is no durability than there is nothing better to ask
for.

(Signed) P. BURTIS CLAYTON
Painting Contractor
Spring Lake, N. J.

2066

Dear Mr. Jordan: Since Mr. Ray founded this busi-
ness over fifty-five years ago, we have always used the
highest quality paints and varnishes, and when some-
thing or nine months ago, we standardized on "Zilo" for
all our exterior painting, we found it to be the best
material we have ever used. It is the only material that
gives us the freedom from any necessity for exact formula-
tions and mixing. I have yet to see any product that is
superior.

"Zilo" represents for the Master Painter a material
that is flexible so that he can make use of his skill in
manipulating the reduction with oil, turpentine and the
other solvents to every requirement that any surface
may demand. It gives him the freedom from any neces-
sity for exact formulae and mixing. I have yet to see any product that is
superior.

We like it in every possible way, because aside from its
appeal to the painter for the reasons I have mentioned
above, it also has its appeal to the owner from the stand-
point of economy. It gives him the freedom from any neces-
sity for exact formulae and mixing. I have yet to see any product that is
superior.

Very truly yours

(Signed) THE HENRY B. RAY CO. INC.
Philadelphia, Pa.

THE SHERWIN-WILLIAMS CO.

ADMINISTRATION OFFICES, CLEVELAND, OHIO

SALES OFFICES, FACTORIES AND WAREHOUSES

IN PRINCIPAL CITIES

PRINTED IN U. S. A.

1915 6-36 1009

ZILO a modern paint pigment BETTER THAN WHITE LEAD



For the Master Painter

0007-SWP-041135

N29016

SHERWIN-WILLIAMS

ZILO

Zilo is the modern paint pigment, of highest quality, made by Sherwin-Williams to give the painter a paste paint possessing the basic advantages found in SWP Sherwin-Williams House Paint.

Zilo is guaranteed to contain nothing but strictly pure white lead carbonate, white lead sulphate and zinc oxide, ground in pure refined linseed oil. (Pure turpentine is included in the Zilo furnished in soft paste consistency.)

COMPOSITION OF LIQUID

Refined Linseed Oil 100%

COMPOSITION OF PIGMENT

Lead Carbonate 66 2/3%
Lead Sulphate 9%
Zinc Oxide 25%
100%

CONTENTS OF PACKAGE BY WEIGHT

Pigment 90%
Liquid 10%
100%

The white lead carbonate used in making S-W Zilo is Sherwin-Williams ODP White Lead -- which may also be bought separately -- the finest quality white lead possible to produce.

There are several well-defined advantages Zilo brings to the painter who uses paste paint to "mix his own":

These advantages are obtained through fortifying white lead carbonate by grinding it together with S-W OZLO. Ozlo is pure white lead sulphate in intimate chemical union with pure zinc oxide so that the white lead and the zinc oxide are, in actuality, one single pigment. Ozlo is made only by Sherwin-Williams in their smelters in Coffeyville, Kansas, from ores taken from Sherwin-Williams mines in New Mexico.

How Does S-W OZLO Fortify White Lead Paint?

1. RESISTS ATMOSPHERIC DISCOLORATION

White lead carbonate is readily affected by sulphur fumes present in the air even in residential sections wherever there is natural gas or wherever coal is burned. A chemical reaction takes place; white lead carbonate is changed to black lead sulphide.

White lead sulphate used in making OZLO is not readily affected by these conditions and zinc oxide -- not at all.

Zilo, fortified by S-W OZLO retains its whiteness longer than a straight white lead (carbonate) paint and tints made with Zilo retain their character and clarity much longer.

2. BETTER WEATHERING CHARACTERISTICS

Progressive painters are now familiar with the benefits derived when white lead paint is "tempered" with zinc oxide. We list them for reference:

1. Control to reduce severity of chalking.
2. Elimination of characteristic lead "check."
3. Smoother paint film -- better retention of gloss.
4. Retention of smoothness due to uniform shallow chalk.
5. Finer general appearance of the job in service, due to freedom from erosion or "washing" which makes a very spotty surface.
6. A more economical material for the painter -- takes more out than lead -- can be spread to a thinner film because of greater opacity and tendency to level without deep brush marking.
7. WASHABILITY -- Zinc paint can be washed clean with soap and water -- much appreciated by the customer.

ZILO PROVIDES ZINC IN MOST DESIRABLE FORM

Zilo gives the painter the desirable features of ready-to-use factory-mixed formulation, combined with paint in paste form, that the painter can make into liquid paint to suit his requirements. In other words, Zilo is the pigment portion of any desired form of paint to be used in exactly the same manner as the painter has always used white lead.

In Zilo, zinc oxide has been combined with white lead, not only in scientifically correct proportions, thoroughly mixed with the white lead in a manner impossible to attain through hand mixing -- BUT -- it is combined, intimately with white lead sulphate so that we have still better whiteness and resistance to discoloration. AND -- what is even more important -- Sherwin-Williams paint chemists have learned from countless tests that Zilo is free from excessive hardness and tendency to crack -- a fault dreaded by painters when zinc oxide is used indiscriminately in house paint.

0007--SWP-041136

0007-SWP-000124529