

CG 01 CODE YE-698-D PKG

LOT E1097

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO. CARS LOADED	EXPLAIN LOSSES
242	4-29-81	5:30 AM	JMH	2	54	92	93	54	54	1ST	2ND	3RD	4TH	5TH								

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 5656

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

YE-698

1097
41
225

12.76 *

3.17 +
0.12 -/
3.20 +
0.12 -/
3.61 +
0.12 -/
9.62 *

1097
124
41

9.62 +
46.94 +
56.56 *

1097
124
41

3.64 +
0.14 -/
3.47 +
0.14 -/
3.51 +
0.14 -/
3.46 +
0.14 -/
3.66 +
0.14 -/
3.28 +
0.14 -/
3.28 +
0.14 -/
3.80 +
0.14 -/
3.56 +
0.14 -/
3.28 +
0.14 -/
3.41 +
0.14 -/
3.47 +
0.14 -/
3.69 +
0.14 -/
3.39 +
0.14 -/
46.94 *