

MO-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

LOT

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

STUMP

TOTAL NET WT.

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

N 31924

12/260  
CG 40 CODE RT-539-D PKG.   
JAN -4 33631  
EST. WGT. 486 LBS.

## PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES  
RT-539-D (N)APPROVED BY  
EWK 10-25-7  
DCG 10-25-7TYPED BY  
JTC 11-15-77

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED DARK

BLEEDING

## INSTRUCTIONS

## -PRESSING-

## RECORD

| VAT          | 260       |                         |  |  | PRESSLOAD       | 1ST  | 2ND | 3RD | 4TH | 5TH |
|--------------|-----------|-------------------------|--|--|-----------------|------|-----|-----|-----|-----|
| DATE         | 1-4-80    | SH                      |  |  | STARTED         | 9PM  |     |     |     |     |
| TIME         | 3:40 PM   |                         |  |  | CAKES USED      | 36   |     |     |     |     |
| RELEASED BY  | AG        |                         |  |  | WATER ON        | 5AM  |     |     |     |     |
| PRESS        | 12        |                         |  |  | HRS. WASHED     | 4    |     |     |     |     |
| NO. OF CAKES | 36        |                         |  |  | OHMS            | 5800 |     |     |     |     |
| PRESS        | WITHOUT   | AGITATION               |  |  | HRS. WASHED     |      |     |     |     |     |
| WASH TO      | 4000      | OHMS WITH 35-75°F WATER |  |  | OHMS            |      |     |     |     |     |
| TEST AFTER   | 4         | HOURS                   |  |  | HRS. WASHED     |      |     |     |     |     |
| LOAD         | ON 3 CARS |                         |  |  | OHMS            |      |     |     |     |     |
|              |           |                         |  |  | CAKE CONDITION  |      |     |     |     |     |
|              |           |                         |  |  | NO. CARS LOADED | 2    |     |     |     |     |
|              |           |                         |  |  | EXPLAIN LOSSES  |      |     |     |     |     |

SAMPLES  
DELIVER TO

SAMPLED BY

RELEASED BY

## -DRYING-

| DRY 20 HRS AT 180°F | LUMP: - OK - WET - SALTS - CONTAMINAT              |
|---------------------|----------------------------------------------------|
| TEMP.               |                                                    |
|                     | all color pulled. No record of any processing loss |
|                     | ADDITIONAL DRYING HOURS REQUIRED                   |

SAMPLES  
DELIVER TONO. CARS PULLED  
SAMPLED BYNO. DRUMS: 4  
LUMP WGT. 464  
RELEASED BY w

## -GRINDING-

| MILL #5 LSP 1/8" RP   | SCREEN 1750 RPM | SCREEN         | RPM     |
|-----------------------|-----------------|----------------|---------|
| MAX. TEMP. 170 °F     |                 | MAX. TEMP.     | °F      |
|                       |                 | EXPLAIN LOSSES | # 49980 |
| SAMPLE WITHOUT MIXING |                 | DATE MIXED     |         |
| SAMPLES 1 Env         |                 | SAMPLED BY     |         |
| DELIVER TO C T L      |                 | RELEASED BY    |         |

DUP050292810


N 31924.01

1.4 4  
1.4 4  
1.5 6  
1.4 4  
1.2 4  
1.1 4  
1.1 4  
4.4 4

N 31924.02

DUP050292811





**N 31924.03**

DUP050292812