

- 2 -

FORMULAE OF SPECIAL PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MINNEAPOLIS, MINN. 2/
Outside White House Paint (P.F.C.M.)
Percentage Formula
Working or Vat Formula
January 1941 to June 1942 2/
January 1941 to June 1942
Percent
Gals. Lbs.

60.1	Standard Zinc	300
	Sublimed White Lead	350
	Titanium Oxide	30
39.2	Asbestine	100
100.0	Marbles	170
	Ultramarine Blue	3 av. oz.
	Bleached Linseed Oil	70
	Clean Spirits	5
	Intense Drier	4
	Solution	2

Inside Flat White Paint (#468)
Percentage Formula
Working or Vat Formula
January 1941 to June 1942 2/
January 1941 to June 1942
Percent
Gals. Lbs.

61.3	Lithophone	600
	Surfex	200
	Asbestine	150
36.7	Aluminum Stearate	3
100.0	Hydroquinone	2 av. oz.
	Heavy Grinding Oil	4
	Bleached Linseed Oil	13
	Flat Paint Grinding Varnish	14
	Clean Spirits	40
	Soligen Lead Drier	4
	Cobalt Drier	2
	Bodying Varnish	1/2

Mr. [redacted] stated that there were no changes in his formulae for the products
January 1941 to June 1942, except those shown for enamel.

Mr. [redacted] working formula.