MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE VH808 LOT 37179

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	22	2203	26	
	STUMP	[illegible]	2199	

TOTAL NET WT. 2203 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
PP	10/3/80	23

N35267



DUP050108342

33/106

CG 46 CODE YT-808-D PKG. ____

SEP·22·80 37179 - X

EST. WGT. 2238 LBS.

2 gs

22

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	EWK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
JLC 10/26/77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
AT		106				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE		9-23-80				STARTED	5 AM				
IME		11:00 A				CAKES USED	60				
ELEASED BY		[illegible]				WATER ON	8 PM				
RESS	32	33	35			HRS. WASHED	4				
O. OF CAKES	60	62	60			OHMS	9000				
RESS	WITHOUT	AGITATION				HRS. WASHED					
ASH TO	4000	OHMS with 35-75°F water				OHMS					
EST AFTER	4	HOURS				HRS. WASHED					
OAD	on 9 cars					OHMS					
						CAKE CONDITION	25	7			
						NO. CARS LOADED					

EXPLAIN LOSSES

AMPLES

ELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 200°F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 16

AMPLES

ELIVER TO

NO. CARS PULLED LUMP WGT. 2199

SAMPLED BY RELEASED BY

-GRINDING-

ILL 4 or 10 HSP 1/8" RB SCREEN 3500 RPM

AX. TEMP. 190 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE WITHOUT MIXING

AMPLES 1 env + 1 Pint can

ELIVER TO C.T.L.

DATE MIXED 10/2/80

SAMPLED BY 271 RELEASED BY

DUP050108343

37179
124
51

1.66 +
0.14 -
1.51 +
0.14 -
1.52 +
0.14 -
1.50 +
0.14 -
1.59 +
0.14 -
1.46 +
0.14 -
1.65 +
0.14 -
1.50 +
0.14 -
1.56 +
0.14 -
1.60 +
0.14 -
1.52 +
0.14 -
1.52 +
0.14 -
16.91 *

12 DRUMS DUMP 7 CAR

16.91 +
1.59 +
0.14 -
1.66 +
0.14 -
1.43 +
0.14 -
0.96 +
0.14 -
21.99 *

4

DUP050108344