

Durafilm Flat
 Interior Wall Paint (Flat)
 White
 T.W.
 First

				Actual 3/31/42		Market 3/31/42		
<u>Pigment</u>								
2132	Calcium Titanium	3486	128.63	5.77	201.14	5.65		196.96
1999	Calcium Carbonate	1056	44.99	1.22	12.88	1.50		15.84
1552	Diatomaceous Silica	342	17.82	2.25	7.70	2.40		8.21
1577	Calcium Linoleate	30	2.55	8.32	2.50	8.00		2.40
547	Aluminum Stearate	30	3.30	25.22	7.57	25.00		7.50
<u>Vehicle</u>								
(27)	Raw Linseed Oil	348	45.03	10.87	37.83	13.07		45.48
(2956)A	Grinding Varnish	158	22.46	9.50	15.96	10.90		18.31
(440)	Drier	84	11.05	5.68	4.77	6.23		5.23
(1157)	Ester Gum Solution	658	70.53	6.97	38.89	7.24		40.40
(904)	Kerosene	1648	235.52	1.48	24.39	1.48		24.39
(9081)	Linseed Oil Reducer	342	45.90	10.70	36.59	11.84		40.49
NW-129	Bodying Oil	30	4.00	32.18	9.65	32.18		9.65
		8122		399.87				414.86
				64.50				66.91

631.78
 1.86%
 620.00

	.645	.669
	.013	.013
	.030	.030
	.688	.712
	.187	.187
	.875	.899

charged to last...

	C.L.	L.C.L.
1A. In a group...	1.63	1.71
1B. In an...	1.38	1.46
1C. By...	1.63	2.65
1D. In an...	1.63	1.71
1E. In other...		1.81

OVER 500
 UNDER 500

OPA ■■■000750

N 4758