Miami 9895 - 9896

REDACTED

(A6) Class 68 05 00

Lead Containing And Lead Free Pigments In A-100 Undercoater

Series 41173 - 41192 was examined and retired after 24 months exposure at Miami, Florida. It includes A6 W 32 and A6 W 28 undercoaters with and without lead carbonate. Zirconium sulfate was added to the lead free formulation as a stain control agent. Regular A-100 is the topcoat.

The results of this series indicate no large difference in performance of lead containing primers compared with lead free primers except in mildew resistance. The lead containing primers were rated one to two points better than the lead free formulation.

BSYT

REDACTED