

(DRY AND PASTE ONLY)

CODE KY-907 LOT 35207

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
------------	---------	-----------	----------	----

1780 1 - T - 299

1810	1 - T - 178	
------	-------------	--

[illegible]

_____ LUMP 3560# _____

STAMP _____
3590

TOTAL NET WT. 50.74 PKG, N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
300	1 11 80	

7,11,80

N32167

CG 03 CODE KY-907-D PKG.

APR 8 35204

EST. WGT. 1080 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-907-D (D)
APPROVED BY
EWK 12/12/77
DCG 12/13/77

TYPED BY
rj 2/6/78

MAKING NOTES

REMARKS

TOTAL WGT. 3480#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT			244		PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			4980		STARTED	1:30 PM				
TIME			11:20 A		CAKES USED	46				
RELEASED BY			323		WATER ON	1:30 PM				
PRESS	2	22	23	24	HRS. WASHED	13				
NO. OF CAKES	46	46	46	52	OHMS	2000				
PRESS with			AGITATION		HRS. WASHED					
WASH TO 2000			OHMS with 135-145°F water		OHMS					
TEST AFTER 2			HOURS		HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	5				
					EXPLAIN LOSSES					

SAMPLES 8oz jar
DELIVER TO CIL for Color

SAMPLED BY 283 RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATED

Dry on first stage only.
Reset every 5 hrs til dry.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 12
LUMP WGT. 3560
RELEASED BY DCC

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

DATE MIXED

SAMPLES 1 ENV & 1 PTCAN

DELIVER TO C T L

SAMPLED BY

RELEASED BY

N32167.01

DUP050456903

35204
41
294

0.00 *
3.27 +
0.14 -
3.27 +
0.14 -
3.27 +
0.14 -
3.29 +
0.14 -
3.32 +
0.14 -
3.33 +
0.14 -
3.25 +
0.14 -
3.24 +
0.14 -
3.20 +
0.14 -
3.21 +
0.14 -
3.23 +
0.14 -
1.40 +
0.14 -
35.60 *
35.60M+

N32167.02

DUP050456904