

157 L

Mr P. 175-180

Pen 77- 32.36 (min)

Pen 115- 75 (map)

527

Mr. 190-200

Pen 77 40-50 min

Pen 115 60-75 map

Crackling mine
17-175 15-40

Caustic

store at 80° in winter
summer takes care of itself

We get it in @ 90° to 100°
solidifies - 56° to 58°

PLAINTIFF'S EXHIBIT

BIR-258

5.3# Caustic is one yr. liquid

+2 out

STANDARD SPECIFICATION

#21 WATERBURY THICK ROPE SINGLES - PLAIN AND

W-TEX

Colors: V. Red - Colonial Green, Bright Red, Black
Hussey 910, W. Green, Brown, Slate Blende, Brown
Blende, Ebony Blue, Blue Blende
Plaint - Snow White, Shell White, Sage Blende,
Ivory Mist, Meadow Mist, Desert Brown, White Gold,
Black Gold, Frost Blende, Gray, Shadow Green,
Shadow Gray, Shadow Blue, Shadow Red
Size: 12" x 16" - Cut-Out 3/8" x 5" - Headlap
2"

Thick But - 6" x 36"
Sq. Ft. Material per Sq. - Gross - 240.0 Sq. Ft.
Net - 236.9 Sq. Ft.

Singles per Sq. - 80, per Bale - 27, 27, 26

Net Wt. per Sq. - 212.15

Net Wt. per Bale - 70.75

1/2" slit each end of shingle, 3" above cut-out
for application.

RAW MATERIALS PER SQ.

Bale - 240 Sq. Ft.

Roll - 204 x 18"

Estimation - 414 - 1895

Coating - 421

Filler - 40%

Surfacing - 411 Glenwood

Packing - 04. 141

Gross Wt. Bale - 240 Sq. Ft. 169.1

Overall - 180 Sq. Ft.

Coating - 421

Filler - 40%

Surfacing - 411 oiled

Gross Wt. per 240 Sq. Ft.

Less Cut-Out - 1.1 Sq. Ft.

Net Wt.

Finishing Materials

Shipping Wt.

NET

24.8

46.1

22.1

14.7

53.5

3.8

169.1

12.2

8.2

30.0

215.5

212.1

212.1

215.0

GROSS

27.7

48.4

23.2

15.4

56.2

4.0

169.1

12.8

8.6

31.5

215.5

212.1

212.1

215.0