MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ky-788 LOT E1376

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1800	1	T-327		
1595	1	T-37		
	STUMP	Lump	3506	

TOTAL NET WT. 3395 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

5/21/81

22

CG 03 CODE KY-788-D PKG. ____

MAY -0-81- 1376

EST. WGT. 960 LBS.

OK / AP

3610

Total Wgt. 3560# Req(_____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

E.C INSTRUCTIONS -PRESSING- RECORD

VAT	243				
DATE	5-13-81				
TIME	10:30A				
RELEASED BY	S.R.				
PRESS	22	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	2:30PM				
CAKES USED	48				
WATER ON	3:30PM				
HRS. WASHED	5 1/2				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLES 1- 8oz JAR

DELIVER TO CTL for Color

SAMPLED BY RELEASED BY [signature]

-DRYING-

Dry 12 hrs at 220 °F

Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No Drums 14

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3506

SAMPLED BY RELEASED BY [signature]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096413

1376
41
17

0.00 *

2.56 +
0.12 -
2.60 +
0.12 -
2.66 +
0.12 -
2.80 +
0.12 -
2.58 +
0.12 -
2.58 +
0.12 -
2.57 +
0.12 -
2.70 +
0.12 -
2.64 +
0.12 -
2.65 +
0.12 -
2.59 +
0.12 -
2.59 +
0.12 -
2.61 +
0.12 -
2.61 +
0.12 -
35.06 *