MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO 789 LOT 33777

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2590	1	T. 92		
	STUMP			

TOTAL NET WT. 2590 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	1/15/80	

25/247

CG 04 CODE KO-789-D PKG. ____

→ JAN 12 33777

EST. WGT. ~~1199~~ 509 LBS.

Total Weight ~~5199#~~ 2909 (Req. _____)

PROCESSING INSTRUCTIONS: BATCH UNI

PROCESSES	APPROVED
KO-789-D (I)	EWK 9-21-7
	DCG 9-21-7
	MTW 10-2-7
TYPED BY	
jlc 10-8-76	

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE Y

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	247				
DATE	1/13/80				
TIME	9.10A				
RELEASED BY	C.S				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	~~48~~ 26	

PRESS with AGITATION

WASH TO 5000 OHMS with 35-75°F water

TEST AFTER 6 HOURS

LOAD on ~~6~~ 4 cars

SAMPLES 1 - 8 oz. jar

DELIVER TO CTL for color

RECORD					
PRESSLOAD	1ST	2ND	3RD	4TH	5T
STARTED	2 PM				
CAKES USED	24				
WATER ON	10 PM				
HRS. WASHED	7				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	2				

EXPLAIN LOSSES

SAMPLED BY 197 RELEASED BY

-DRYING-

DRY 16 HOURS AT 220°F L.V. H.V.

LUMP: - OK - WET - SALTS - CONTAMINAT

all color pulled. No record of any processing loss

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 8

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 2663

SAMPLED BY

RELEASED BY

-GRINDING-

MILL 938 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 210 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env. + 1 Pint Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050095351

33777
41
17

0.00 *

3.52 +
0.12 -
3.27 +
0.12 -
3.30 +
0.12 -
3.73 +
0.12 -
3.44 +
0.12 -
3.39 +
0.12 -
3.16 +
0.12 -
3.78 +
0.12 -
26.63 *



DUP050095352