MD-3-A


PACKAGE TICKET (DRY AND PASTE ONLY)

CODE RF792- LOT E1264

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	18	1858	16-20	
	STUMP		1813	

TOTAL NET WT. 1848 PKG. N-CODE

PROD. SPVR.	DATE	WHSE. OPER.
RP	5/15/84	23



O.T

102.+
127.+
121.+
103.+
95.+
103.+
109.+
116.+
100.+
107.+
93.+
97.+
92.+
104.+
96.+
105.+
95.+
78.+
1843.T

O A PANLOAD

CG 16 CODE RT-792-D PKG.

→ MAY -0-81-E-1264

EST. WGT. ~~1800~~ 1765 LBS.

N-7609-A Lot 397, 1758 #, 19 drums

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-792-D (U)	BBK 02-23-77
	DCG 03-15-77
TYPED BY	
emw051777	

MAKING NOTES

REMARKS

NAME: MONASTRAL® MAROON NON-BLEEDING

INSTRUCTIONS

VAT						
DATE						
TIME						
RELEASED BY						
PRESS						
NO. OF CAKES						

PRESS AGITATION
WASH TO OHMS
TEST AFTER ? HOURS
LOAD on 8 cars

NOTE: Cake Condition:

SAMPLES
DELIVER TO

-PRESSING-

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED					
CAKES USED					
WATER ON					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	2	3			
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY RELEASED BY BLL

-DRYING-

Dry 20 Hrs at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATE

Dryer sections used: 1

ADDITIONAL DRYING HOURS REQUIRED

No. Drums: 14

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 1813

SAMPLED BY RELEASED BY JAS

-GRINDING-

MILL#1 HSP 0.066 RP SCREEN 3480 RPM
MAX. TEMP. 150°F

Pulverize with O# N-947-B

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO C T L

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED 5/15/81

SAMPLED BY 213 RELEASED BY

DUP050097127

1264
51
100

1.55 +
0.14 -
1.55 +
0.14 -
1.61 +
0.14 -
1.60 +
0.14 -
1.57 +
0.14 -
1.57 +
0.14 -
8.61 *
8.61M+

1264
51
305

0.00 *
0.00M+

8.61 +
1.53 +
0.14 -
1.55 +
0.14 -
1.46 +
0.14 -
1.51 +
0.14 -
1.18 +
0.14 -
1.48 +
0.14 -
1.49 +
0.14 -
0.44 +
0.14 -
18.13 *
18.13M+

DUP050097128