

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE F-113LOT 36129

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PG

716669**STUMP**Levent1706

TOTAL NET WT.

1666

PKG. N-CODE

PROD. SPVR

DATE

WHSE. OPER.

[Signature]6-7-71160

N32279

DUID050457385

D.T

263.+
251.+
257.+
213.+
297.+
253.+
132.+
1666.T

N32279.01

DUP050457386

CG 08 CODE F-113-D PKG.

JUNE 17 36129

EST. WGT. 1658 LBS.

PRESSROOM:

Record: * Starting inches 80"

* Inches remaining after
1st pressload 36"

PROCESSING INSTRUCTIONS, BATCH UNIT

PROCESSES	APPROVED BY
F-113-D (H)	JMC 01-20-77
	DCG 01-31-77

TYPED BY
01W072977

MAKING NOTES

REMARKS

NAME: AURIC BROWN

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH	WASH TO	TEST AFTER	LOAD	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO. CARS LOADED	EXPLAIN LOSSES
135	6/17/80	11:00 AM			2 x 30		3500	3	on 2 cars		1:30 PM	30	30	30	3500	9000					2	

SAMPLES
DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

Dry 48 hrs at 180°F
Cool to 100°F
Check dryness

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No. Drums:

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYLUMP WGT. 1706
RELEASED BY

-GRINDING-

MILL 10 HSP 1/8" RP SCREEN 3560 RPM
MAX. TEMP. 150°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 2 Env & 2 Pt Cans
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

N32279.02

DUP050457387

36129
51
294

0.00 *

2.48 +
0.12 -
2.93 +
0.12 -
3.13 +
0.12 -
1.80 +
0.12 -
9.86 *

36129
51
158

0.00 *

9.86 +
3.32 +
0.14 -
3.32 +
0.14 -
0.98 +
0.14 -
17.06 *

N32279.03

DUP050457388