MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-787 LOT 38424

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1618	1	T-32		
1554	1	T-178		
	STUMP LUMP		3235	

TOTAL NET WT. 3172 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

1/2/81

N34749

23/944

CG 03 CCDE KY-787-D PKG. _____

→ DEC 30 80 38424

EST. WGT. ~~1090~~ LBS.

Total Wgt. ~~3490#~~ 3332

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (B)	FWK 9/22/76
Alternate	DCG 9/27/76
TYPED BY	
NF 2/12/77	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM — NON-BLEEDING

INSTRUCTIONS EC — -PRESSING- — RECORD

VAT				244	
DATE				12-30	
TIME				2 AM	
RELEASED BY				SJ	
PRESS	22	23	14	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	5 00 PM				
CAKES USED	46				
WATER ON	2 PM				
HRS. WASHED	5H				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLES 1-8 oz JAR

DELIVER TO ctl for color

SAMPLED BY [illegible] RELEASED BY [illegible]

-DRYING-

Dry 12 hrs at 220 °F.
Then Dry 8 hrs at 150°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No. Drums 13

SAMPLES

DELIVER TO

NO. CARS PULLED

LUMP WGT. 3235

SAMPLED BY

RELEASED BY [illegible]

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 ENV & 1 Pt. can

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050105169

38424
41
18

0.00	*
2.70	+
0.14	-
2.76	+
0.14	-
2.95	+
0.14	-
2.42	+
0.14	-
2.56	+
0.14	-
2.57	+
0.14	-
2.58	*
0.14	-
2.78	+
0.14	-
2.56	+
0.14	-
2.60	+
0.14	-
2.56	+
0.14	-
2.81	+
0.14	-
2.32	+
0.14	-
32.35	*

DUP050105170