VISCOSITY WORK SHEET

Item 2608 | P.T.No. | Date 2-25-55 (3-2-55 Running Weights)

Worker NH L.KAY | Polymer Dacron | Solvent Fanal

For Gall | Charge 1272 | Temperature 25°C

Viscometer No. 1 | Efflux Time 89.2 | Weight: Gross 5.2023

Viscometer No. 4 | Efflux Time 99.1 | Tare 5.0773

Viscometer No. 606 612 | Efflux Time 206.6 219.1 | Net .1250

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Inh.visc. Visc.	or M.W.	
4757-67-1	H13	1	138.6; 138.7; 138.7	1.556	0.89	✓ slight gel
"	KR	4	154.4; 154.5; 154.6	1.559	0.89	
" " -2	14	606	324.3; 324.4; 324.3	1.571	0.91	✓
"	H16	612	346.3; 345.6; 346.2; 346.2	1.581	0.92	
" " -3	OP	1	151.5; 152.2; 151.7; 151.8	1.700	1.06	✓
"	93	4	166.2; 166.5; 166.7; 166.5	1.681	1.04	1.05
" " -4	V	606	332.6; 333.3; 332.8; 332.7	1.610	0.95	✓
"	MT	612	353.0; 352.7; 352.7	1.611	0.96	
" " -5	X	1	145.1; 145.1	1.629	0.98	✓
"	N	4	162.0; 162.0	1.626	0.97	
" " -6	W	606	315.0; 314.7; 314.7	1.521	0.84	✓
"	H	612	332.1; 331.7; 331.7	1.512	0.83	
" " -7	GV	606	309.8; 309.8	1.498	0.81	✓
"	1-1	612	329.4; 330.2; 329.4	1.501	0.81	
			(SLIGHT GELL ALL SAMPLES)			

PC-1

N38632