PLAINTIFF'S EXHIBIT

CT-1401

Pipe & Plastics Group

PIPE MACHINE REPORT

MACHINE NO 2 | DATE 3-23-81

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS	1ST SHIFT
12-3500	145		
12-2400	277		
10-3500	175		
10-2400	17		
10-3300 GS	20		
BRUNSWICK	4	9.94 × 11.25	
BRUNSWICK	3	10.50 × 12.25	
BRUNSWICK	2	7.75 × 9.00	

TONS PER	SHIFT	HOUR	GROSS TIME	DOWN TIME	NET TIME	FELT NO.		HOURS
	91.71	9.41	10	0	10	TOP	73033	87¼
						BOT	53381	10

117.3% FOREMAN C. Simmons

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS	2ND SHIFT
		27.5% of Fiber 5500 Blue / Blue	12.8% of 12.2% Fiber Raw Material

TONS PER	SHIFT	HOUR	GROSS TIME	DOWN TIME	NET TIME	FELT NO.		HOURS
						TOP		
						BOT		

FOREMAN

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS	3RD SHIFT

TONS PER	SHIFT	HOUR	GROSS TIME	DOWN TIME	NET TIME	FELT NO.		HOURS
						TOP		
						BOT		

RAW MATERIAL USAGE

BLEND NO.	3 / 5						
FORMULA NO.	13 / 23						

RAW MATERIALS	TOTAL USAGE (LBS.) 1ST SHIFT	2ND SHIFT	3RD SHIFT	DAILY TOTAL	UNIT STANDARD COST	EXTENDED STANDARD COST	ACCUMULATED USAGE TO DATE
C & G 3							
C & G 4							
C & G 5							
AK	2400			2400	.48176	1156.22	5670
AX							
TAK							
S3							
41500	7700			7700	.36995	2787.02	
SR750	4400			4400	.24695	1086.58	5
ML-6	1760			1760	.37602	661.80	
PS					.37602		
MS-6	3740			3740 / 20000	.30852	1153.86	500
CEMENT	75060			75060	.02736	2053.64	93/300
SILICA	48600			48600	.01595	775.17	6030
FINES	12690			12690			1237
DAILY TOTAL				156350		9674.29	
BROUGHT FORWARD			1808405			134490.44	
ACCUM.			1964755			144164.73	196475

	NO PCS MFD.	TOTAL FEET	TOTAL WEIGHT	TOTAL EXTD. STANDARD COST
DAILY TOTALS	643	8359	183427	9789.93
BROUGHT FORWARD	5454	70902	2098983	135861.77
ACCUMULATED TOTALS	6097	79261	2282410	145654.70

	DAILY	ACCUM.
TOTAL FIBER BLENDS	21000	306730
TOTAL FIBER BATCHES	22140	312275

DAILY YIELD	DAILY VARIATION	ACCUMULATED VARIATION
117.3	$ 115.64	$ 1489.97

	GROSS HOURS	NET HOURS	TONS	TONS HR
DAILY	9.75	9.75	91.71	9.41
ACCUM.	126.75	129.75	1196.21	9.30

CTD019394

Pipe & Plastics Group

PIPE MACHINE REPORT

MACHINE NO	DATE
2	3-24-81

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS — 1ST SHIFT
10-2400	194	Burst @ one tunnel take out
12-2400	420	Y4® ✓
10-3000	40	✓
8-2400	68	✓

TONS PER	SHIFT	HOUR	GROSS TIME: 10	FELT NO	HOURS
	93.69	9.61	DOWN TIME: 1/4	TOP 73033	97
			NET TIME: 9 3/4	BOT 53351	193/4
114.4%			FOREMAN C. Simmons		

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS — 2ND SHIFT

TONS PER	SHIFT	HOUR	GROSS TIME:	FELT NO.	HOURS
			DOWN TIME:	TOP	
			NET TIME:	BOT	
			FOREMAN		

SIZE & CLASS	NO. PCS. MFR'D	COMMENTS — 3RD SHIFT

TONS PER	SHIFT	HOUR	GROSS TIME:	FELT NO.	HOURS
			DOWN TIME:	TOP	
			NET TIME:	BOT	
			FOREMAN		

RAW MATERIAL USAGE

BLEND NO.	9		
FORMULA NO.	23		

RAW MATERIALS	TOTAL USAGE (LBS.) 1ST SHIFT	2ND SHIFT	3RD SHIFT	DAILY TOTAL	UNIT STANDARD COST	EXTENDED STANDARD COST	ACCUMULATED USAGE TO DATE
C & G 3							
C & G 4							
C & G 5							
AK	2700			2700	.48176	1300.75	59400
AX							
TAK							
S3							
4T500	7920	180		7920	.36195	2866.64	108790
5R750	4950			4950	.24695	1222.40	62810
ML-6					.37602		3?270
Ps	1980	Fiber 3.7% of Fiber		1980	.37602	744.52	396?
795-6	4950			4950	.30852	1527.17	55000
	1650			22600			
CEMENT	77840			77840	.02736	2129.70	1009140
SILICA	50400			50400	.01595	803.88	653?0
FINES	13075			13075			13?800
DAILY TOTAL				163815		10595.06	
BROUGHT FORWARD			1964755			144164.73	
ACCUM.			2128570			154759.79	2128570

	NO PCS MFD	TOTAL FEET	TOTAL WEIGHT	TOTAL EXTD STANDARD COST
DAILY TOTALS	722	9384	187370	10022.94
BROUGHT FORWARD	6097	79261	2282410	145?54.70
ACCUMULATED TOTALS	6819	88647	2469780	155677.64

		DAILY		ACCUM.
TOTAL FIBER BLENDS		22500		329230
TOTAL FIBER BATCHES		22765		335040

116

DAILY YIELD	DAILY VARIATION	ACCUMULATED VARIATION
114.4	$ 572.12	$ 917.85

	GROSS HOURS	NET HOURS	TONS	TONS HR
DAILY	9.75	9.75	93.69	961
ACCUM.	136.50	133.50	1234.89	905

CTD019395

file

				5/81	3/81	12/79	1/80
3/23/81 —							
Press Apex - C. Northington							
092	6:33 - 9:16	163		.78	0.67		
151	9:16 - 1:02	226		.27	>3.13	>1.6	
144	1:02 - 3:41	159		.39	>5.68	1.9	
	TWA	548		.45	3.14 f/cc	1.7	
					>4.98		
Mandrel Handler - J. Mascola							
093	6:42 - 1:05	383		0072	>0.86	0.65	
148	1:05 - 3:51	166		0.038	0.68	0.96	
	TWA	549		0.049	0.81 f/cc	0.75	
3/24/81							
Press Apex - C. Northington							
136	7:47 - 10:42	175			>4.98		
Console Area							
132	7:50 - 10:41	171		0.07	1.72	2.1	.37
				0.22		1.4	4.69
				0.10			
				0.17			
Rollup Area							
130	7:48 - 10:41	173		1.32	>2.66	>7.3	.41
				>0.57			.20
				>0.16			.61

Felt hours:

3/23/81 Top 87 hours Bottom new

12/3/79 Top 93 hours Bottom 115 hours

1/28/80 new felt put on 6:00 - 6:45a Bottom/Top?

CTD019396

5/8 - 1 E.

Line 3

18" 5000 ✓ C/R ✓
P/B - 13' ✓
1534' - 42
C –
R –
SB –

18" 5000 ✓
F/B - 13' ✓
1963 – 47
C –
R –
SB –

18" 3300 ✓
P/B - 13' ✓
728 - 56
C –
R –
SB –

Wetsaw 18 ✓ 1/4 ✓ from

18" 5000 ✓ line 3
1/2 MEC ✓ / – ✓
260' - 40
SB –

18" 5000
1/4 MEC ✓
78' 24
SB –

21" 3300 Lehman
1/4 MEC N/S ✓
52' - 16
SB –

21" 5000
1/4 MEC N/S
12' - 4
SB –

10" 200
THO 3 ✓ –
39 Nibel

18" 5000
CPLG ✓
10954BM

18" 3300
CPLG ✓
15 Chic

21" 5000
CPLG N/S ✓
75 Chic

Received Hillsboro 3/23 12" ✓

21 X 6
TEE ✓
1

21 X 4
TEE ✓
5

6" 90°
ELBOW ✓
74

8" 90°
ELBOW ✓
55

Epoxy –

Rod 8 x 4 ✓

Pencil Sharp. 8" 1/4 ✓

5" 3300
1/4 FTGS ✓
162.5' - 50

CTD019397

3/23/81

Line #3

N/S
21" 5000
P/B - 13 ✓
1443' - 111
C —
R —
SB —

N/S
21" 4000
P/B - 13 ✓
1599' - 123
C —
R —
SB —

N/S
21" 5000
1/2 MEO ✓
208' - 32
SB —

Lateral

N/S
21" 5000
6' MEO ✓
24' - 4
SB —

N/S
21" 5000
1/4 MEO ✓
136.5' - 42
SB —

64 BM

18" 5000
CPLG X ✓
202

Epoxy

8X5
TEE ✓
80

6" 30°
ELBOW ✓
79

4" 30°
ELBOW ✓
224

12X12
XH WYE ✓
6

8" 3300
1/4 SCRAP ✓
19.5 - 6

8" 3300
1/4 FTGS. ✓
425.8' - 131

CTD019398

3/23/81

Vat Temp 72°
Tunnel 228/160

50 Total
5500 #

#23 10# 2 Kinds
7 Blue 770#
Tenderloin (4%)

Time 235 Filter 410 Butts 2935
Total 3500 30.8%

3/24/81

Vat Temp 70
Tunnel 230/160

Time #23 Filtered /53 butts

#12 0 Kinds / 3 butts

63 Total
6930#

Alk 6.5 PH 12.1
Sludge 2.3% 630a

#23 7 Blue 770# ~~2500~~ 30.8

Time 285 Filter 380 Butts 2905

#12 Hit 70 Fourth time

CTD019400