

PRODUCT NAME: MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YC-16-B PKG _____

PROCESSES
YC-16-B (C)

APPROVED BY:
FWF 09/22/81

LOT K2H14 SEP 27 1982

COMTYF JOB NAME: 01YC016BPC

EST. WT: 3098* LBS

MAKING NOTES:

INSTRUCTIONS

= PRESSING =

RECORD

VAT							PRESS LOAD					1ST	2ND	3RD	4TH	5TH					
DATE							STARTED							4PM							
TIME							CAKES USED							38							
RELEASED BY							WATER ON							7PM							
PRESS							191	92	93	2	25	HRS. WASHED									
NO. OF CAKES							42	32	32	32	32	M MHOS									
PRESS WITH AGITATION							HRS. WASHED							2 1/2							
WASH TO 500 M MHOS WITH 35-75% WATER							M MHOS							220							
TEST AFTER 2 HOURS							HRS. WASHED														
LOAD ON 4 CARS							M MHOS														
-----							CAKE CONDITION														
-----							NO CARS LOADED							6							
-----							EXPLAIN LOSSES														

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

DRY 16 HOURS AT 220* F.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO -

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 12
LUMP WGT 3342

= GRINDING =

MIKROATOMIZE
SET ROOF GATE AT 2 INCHES AIR FLOW
SET LUMP FEED SCREW AT 1/2 SPEED
MAGNETIC READING ON ATOMIZER
PANEL 1-0*

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

14
41
427

0.00 *
2.79 +
0.12 ✓
3.04 +
0.12 ✓
2.84 +
0.12 ✓
2.82 +
0.12 ✓
3.01 +
0.12 ✓
2.94 +
0.12 ✓
3.04 +
0.12 ✓
3.05 +
0.12 ✓
3.05 +
0.12 ✓
3.04 +
0.12 ✓
2.96 +
0.12 ✓
2.28 +
0.12 ✓
33.42 *