MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE BT428 LOT 37224

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	32	3056	64	
	[redacted]	LUMP	3049	

TOTAL NET WT. 3056 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

11/01

N35085

DUP050107580



DUP050107581

96
901

CG 32 CODE RT-428-D PKG. ____

→ NOV -4 80 37724

EST. WGT. 3068 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-428-D (V)	JJG 12-10-76
	DCG 08-10-78
TYPED BY	
emw081878	

MAKING NOTES

REMARKS

NAME: WATCHUNG® RED B

NON-BLEEDING

-PRESSING-

INSTRUCTIONS						RECORD					
VAT	901					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	10-4-80	RM				STARTED	2:00 AM				
TIME	10:45 P.M					CAKES USED	88				
RELEASED BY	E.M					WATER ON	12 PM				
PRESS	95	96				HRS. WASHED	6				
NO. OF CAKES	76	88				OHMS	8000				
PRESS	with	AGITATION				HRS. WASHED					
WASH TO	3000	OHMS with 35-75°F water				OHMS					
TEST AFTER	3	HOURS				HRS. WASHED					
LOAD on 10 cars						OHMS					
1. Press Immediately Code						CAKE CONDITION					
2. Instruct Making Area to add 10# N-588-A halfway thru pressing						NO. CARS LOADED	5+6				
3. Clean magnetic separator after pressing. Cleaned by 85 Time cleaned 12 PM						EXPLAIN LOSSES					
SAMPLES											
DELIVER TO						SAMPLED BY 3[illegible]		RELEASED BY			

-DRYING-

DRY 24 HOURS AT 220 °F	LUMP: - OK - WET - SALTS - CONTAMINATE
Hold on track 30 min before dumping	
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS 22
SAMPLES	NO. CARS PULLED — LUMP WGT. 3049
DELIVER TO	SAMPLED BY — RELEASED BY DC

-GRINDING-

MILL 2 HSP 1/8" RP SCREEN 3350 RPM	SCREEN RPM
MAX. TEMP. 150°F	MAX. TEMP. °F
	EXPLAIN LOSSES
SAMPLE WITHOUT MIXING	DATE MIXED 221
SAMPLES 2 Env	
DELIVER TO C T L	SAMPLED BY — RELEASED BY

DUP050107582

37724

51

0

166
14
160
14
167
14
167
14
157
14
148
14
160
14
147
14
153
14
158
14
164
14
144
14
163
14
151
14
146
14
149
14
146
14
150
14
152
14
160
14
159
14
90
14
3049

12 DRUMS

DUP050107583