

SUBJECT:

APR 1 10 0 21 AM
MAR 28 1892

100 Canal Street, CLEVELAND.

March 23, 1892.

H. A. Sherwin,

My Dear Sir:-

Another test of the Dahl Lead has been made and strange to say, the test shows up very much like the test made last summer. The Dahl Lead takes twice as much oil to grind it and 50 percent more to thin it. When thinned a gallon of paint made with the regular lead weighs 20 1/2 lbs., a gal. of paint made with the Dahl Lead weighs 17 lbs. The Dahl Lead was still thicker than the regular and brushes and works very much like zinc. On one coat the regular Lead shows most body though on the two coat work there is a little difference because either covers perfectly. The regular Lead dries several hours quicker than the Dahl Lead. In view of this peculiar showing, I would suggest the making of another lot in liquid form.

J. H. Edwards
MAR 23 1892

0007-SWP-043390

N23207