241 EST. WGT. 3371 LBS.

OK/R

TYPED BY
JLC 11-24-76

MAKING NOTES

REMARKS

ME: MOLYBDATE ORANGE

NON-BLEEDING

INSTRUCTIONS E.C.

-PRESSING-

| | | | | | |
|---|---|---|---|---|---|
| AT | | | 2.41 | | |
| ATE | | | 4.15 | | |
| ME | | | 6.40A | | |
| LEASED BY | | | MB | | |
| RESS | 2 | 91 | 92 | 93 | |
| O. OF CAKES | 32 | 42 | 32 | 32 | |

RESS with AGITATION
ASH TO 2000 OHMS with 35-75°F water
EST AFTER 2 HOURS
OAD on 4 cars

RECORD

| PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
|---|---|---|---|---|---|
| STARTED | 8 | | | | |
| CAKES USED | 34 | | | | |
| WATER ON | 120 | | | | |
| HRS. WASHED | 2 | | | | |
| OHMS | 2500 | | | | |
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| CAKE CONDITION | | | | | |
| NO. CARS LOADED | 4 | | | | |

EXPLAIN LOSSES

MPLES
ELIVER TO

SAMPLED BY RELEASED BY BLL

-DRYING-

XTRUDED) DRY 12 HOURS AT 240°F
OT EXTRUDED) DRY 14 HOURS AT 240°F

LUMP: - OK - WET - SALTS - CONTAMINATED
Color appears dry [illegible] released.

ADDITIONAL DRYING HOURS REQUIRED

No Drums 11

MPLES
LIVER TO

NO. CARS PULLED LUMP WGT. 3504
SAMPLED BY RELEASED BY RH

-GRINDING-

LL Mikroatomize SCREEN RPM
AX. TEMP. °F

SET ROOF BLAST GATE AT "9" FOR
HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE A[illegible] / WITHOUT MIXING
AMPLES 1 Env
ELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

1042
4100
158

0.00 *

3.09 +
0.12
3.19 +
0.12
3.26 +
0.12
2.98 +
0.12
3.16 +
0.12
3.45 +
0.12
3.43 +
0.12
3.42 +
0.12
3.60 +
0.12
3.30 +
0.12
3.48 +
0.12
35.04 *

DUP050096071