MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE YT808 LOT E1554

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	11	1334	36	
	STUMP	Lump	1343	

TOTAL NET WT. 1334 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[signature]	6/19	160



DUP050098645

DRY OUT CARD

CG 46 CODE YT-808-D PKG.

MAY -0-81-E1554

EST. WGT. ~~2230~~ 0 LBS.

15504

Pan Lot of ~~15504~~ # 100

YC11A Lot ~~33354~~ 35353 #

Dryout

Total Wgt - ~~15504~~ 15504 #

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
YT-808-D (D)	EMK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
JIC 10/26/77	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW BLEEDING

INSTRUCTIONS -PRESSING- RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
AT						STARTED					
ATE						CAKES USED					
IME						WATER ON					
ELEASED BY						HRS. WASHED					
RESS	32	33	35			OHMS					
O. OF CAKES	60	62	60			HRS. WASHED					
RESS	WITHOUT	AGITATION				OHMS					
ASH TO	4000	OHMS with 35-75°F water				HRS. WASHED					
EST AFTER	4	HOURS				OHMS					
OAD	on 9 cars					CAKE CONDITION					
						NO. CARS LOADED	2				
						EXPLAIN LOSSES					
AMPLES											
ELIVER TO						SAMPLED BY		RELEASED BY			

-DRYING-

DRY 24 HOURS AT 200°F

LUMP: - OK - WET - SALTS - CONTAMINATED

P/K from drums not listed on any Processing Record

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 11

AMPLES NO. CARS PULLED LUMP WGT. 1343

ELIVER TO SAMPLED BY RELEASED BY

-GRINDING-

ILL 4 or 10 HSP 1/8"RB SCREEN 3500 RPM

AX. TEMP. 190 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE WITHOUT MIXING

AMPLES 1 env + 1 Pint can

ELIVER TO CTL

DATE MIXED 6-19-81

SAMPLED BY RELEASED BY

DUP050098646

554
1
31

0.00 *

1.60 +
0.14 -/
1.50 +
0.14 -/
1.32 +
0.14 -/
1.55 +
0.14 -/
1.55 +
0.14 -/
1.40 +
0.14 -/
0.40 +
0.14 -/
8.34 *

8.34 +
1.48 +
0.12 -/
1.61 +
0.12 -/
1.55 +
0.12 -/
0.93 +
0.12 -/
13.43 *

DUP050098647