MD-3-A

PACKAGE TICKET

CODE BT284 LOT G24-72

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		12	1782	9

STUMP

TOTAL NET WT. 1782

LUMP WT. 1687 PKG. N-CODE

PROD. SUPV. DATE 7-29-82 OPERATOR 23

N32660

Finishing: Co-Pub with N-128-A & No FS

PRODUCT NAME = MONASTRAL BLUE B — DATE PRINTED: 1/06/82

CC 20 CODE BT-284-D PKG — PROCESSES: BT-284-D (R) — APPROVED BY:

JUL 1 1982 (DATE) G2H72 (LOT) — TYPED BY: JMH

EST.WT. ~~2000~~ 1785 LBS. (11) — JOB NAME: 20BT284DPG

INSTRUCTIONS	= PRESSING =		RECORD				
				1ST	2ND	3RD	4TH	5TH
VAT			PRESSLOAD					
DATE			STARTED					
TIME			CAKES USED					
RELEASED BY			WATER ON					
PRESS	9+10	17 + 18	HRS. WASHED					
NO.OF CAKES	2X119 + 43	3 X 84 + 28	OHMS					
PRESS WITH AGITATION			HRS. WASHED					
WASH TO OHMS -			OHMS					
TEST AFTER HOURS			HRS. WASHED					
LOAD ON 8 CARS			OHMS					
			CAKE CONDITION					
			NO CARS LOADED	6				
			EXPLAIN LOSSES					
SAMPLES JAR			SAMPLED BY					
DELIVERED TO			RELEASED BY	RH				

= DRYING =

DRY 16 HOURS @ 220°F

JUMP: OK - WET - SALTS - CONTAMINATD

No record of any problems. Losses Compare acceptable for last cycle.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO CARS PULLED

SAMPLED BY

RELEASED BY AR

NO DRUMS 10

LUMP WGT 1687

= GRINDING =

MILL 3 HR BLSP 3/32"RP SCREEN 1785RPM

MAX. TEMP 140 DEG F

INERT MILL WITH CO2 WHEN GRINDING PER OP #0042

Co-Pub with 133# N-128-A Blanc Fixe

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE AFTER ~~WASH~~ MIXING

SAMPLE 1 ENT & 1 PT CAN

DELIVER TO CTL

DATE MIXED 9-9-82

SAMPLED BY

RELEASED BY

N32660.01

DUP050463881

72
51
158

1.39 +
0.12 -
1.83 +
0.12 -
1.23 +
0.12 -
1.85 +
0.12 -
1.84 +
0.12 -
1.89 +
0.12 -
1.93 +
0.12 -
1.83 +
0.12 -
1.93 +
0.12 -
1.90 +
0.12 -
0.57 +
0.12 -
16.87 *

1·29 +
1·22 +
1·53 +
1·30 +
1·62 +
1·63 +
2·06 +
1·57 +
1·50 +
1·38 +
1·31 +
1·41 +

012

17·82 ↳

N32660.02

DUP050463882