

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81

LOT MAY -0-81-E-1431

ALTERNATE
TYPED BY JMH

EST'D WGT 5632

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YE698DPS

INSTRUCTIONS			= PRESSING =	RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
				2	54																	

SAMPLES
DELIVER TOSAMPLED BY
RELEASED BY

= DRYING =		= GRINDING =	
(EXTRUDED) DRY 10 HRS AT 240 DEG F	LUMP: - OK - WET - SALTS - CONTAMINATED	MILL MIKROATOMIZE	SCREEN
(NOT EXTRUDED) DRY 10 HRS AT 240 F		MAX. TEMP	DEG F

SAMPLES 1 ENV
DELIVER TO COLOR TEST LABNO CARS PULLED 6
SAMPLED BY 17
RELEASED BY LSVNO DRUMS 15
LUMP WGT 5167

= GRINDING =		= GRINDING =	
MILL MIKROATOMIZE	SCREEN	RPM	SCREEN
MAX. TEMP	DEG F	MAX. TEMP	F

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1431
4100
17

0.00 *

3.48 +
0.12 -
3.80 +
0.12 -
3.82 +
0.12 -
3.44 +
0.12 -
3.57 +
0.12 -
3.73 +
0.12 -
3.56 +
0.12 -
3.71 +
0.12 -
3.57 +
0.12 -
3.55 +
0.12 -
3.60 +
0.12 -
3.66 +
0.12 -
3.59 +
0.12 -
3.48 +
0.12 -
2.91 +
0.12 -
51.67 *

YE 698D
LOT 1427

6001