

CR-164

CKR CRC (COMPAR) CKR-

PHYSICAL TEST SHEET

STOCK PVN072+163 MIXED CRC FACT6-18-86 CURED 7-29-86 TESTED 7-30-86
CRC V-3260+V-3259

CURE	STOCK THICK	LBS. %	LBS. %	LBS. %	LBS. %	SET BREAK	TENS. 100% MOD	TENS %	TENS TEAR B	TENS TEAR C	TENS. BREAK	ELONG	HARD-NESS	SET
CRC 1	.080					200	750				1500	300	78-70	
PVN 072 2	.079					197	800				1550	300		
V-3260 3	.077					193	700				1500	300		
TEAR 1	.084					210			331					
B 2	.082					205			313					
TEAR 1	.088					220				213				
C 2	.087					217				206				
CKR 1	.087					217	600				1600	350	71-69	
PVN 072 2	.087					217	600				1550	350		
3	.088					220	600				1600	340		
TEAR 1	.088					220			275					
B 2	.088					220			250					
TEAR 1	.087					217				175				
C 2	.085					213				181				
CRC 1	.079					197	1800				3000	250	91-90	
PVN 163 2	.078					195	1900				3075	250		
V-3259 3	.080					200	1850				3000	250		
TEAR 1	.082					205			588					
B 2	.080					200			575					
TEAR 1	.084					210				413				
C 2	.086					215				425				
CKR 1	.092					230	1500				3050	275	85-81	
PVN 163 2	.092					230	1450				3000	280		
3	.093					232	1550				3050	280		
TEAR 1	.092					230			489					
B 2	.092					230			400					
TEAR 1	.091					227				325				
C 2	.091					227				313				

CHARD0 02243

OK! CRC

PHYSICAL TEST SHEET

STOCK 072163

MIXED

CURED 7-31-86

TESTED 7-31-86

[illegible]

CHARDO 02244