MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 181 LOT 374-01

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1558	1	T - 93		
1586	1	T - 281		
	STUMP	Lumi. 3144		

TOTAL NET WT. 3144 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
CT	10/16/80	

N34994

22/240

CG 03 CODE KY-787-D PKG. ____

→ OCT-10-80 37401

EST. WGT. 1990 LBS.

ak/HP

TOTAL WGT 3332#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPED BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

-PRESSING-

INSTRUCTIONS					
VAT	240				
DATE	10-13-80				
TIME	7:21				
RELEASED BY					
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	

PRESS WITH AGITATION

WASH TO 2000 OHMS WITH 35-75 F WATER

TEST AFTER 2 HOURS

LOAD ON 6 CARS

TDS

SAMPLES 1-8 OZ JAR

DELIVER TO CTL FOR COLOR

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:30				
CAKES USED	52				
WATER ON	4 AM				
HRS. WASHED	4				
OHMS	4000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	3+2				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY TDS

-DRYING-

DRY 12 HRS AT 220 °F

THEN DRY 6 HRS AT 160 °F

SAMPLES

DELIVER TO

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

NO. CARS PULLED LUMP WGT. 3144

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT. CAN

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050106121

37401
41
52

0.00 *

2.70 +
0.12 -
2.69 +
0.12 -
2.79 +
0.12 -
2.77 +
0.12 -
2.72 +
0.12 -
2.76 +
0.12 -
2.86 +
0.12 -
2.83 +
0.12 -
2.86 +
0.12 -
2.68 +
0.12 -
2.49 +
0.12 -
2.73 +
0.12 -
31.44 *

DUP050106122