

PRODUCT NAME = MOLYBDATE, ORANGE

NON-BLEEDING

CG 01 CODE YE-698-D PKG _____

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

LOT MAY -0-81-E-1431

EST'D WGT 5632

MAKING NOTES

TOTAL EST'D WGT= LBS (CRT ENTRY)

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT		245	
DATE		5-18	
TIME		545	
RELEASED BY		SA	
PRESS	2	92	93
NO. OF CAKES	54	54	54
PRESS WITH AGITATION			
WASH TO 2000 OHMS WITH		35-75 F	WATER
TEST AFTER	2 HOURS		
LOAD ON	7 CARS		

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	7 PM				
CAKES USED	54				
WATER ON	10:30 PM				
HRS. WASHED	3				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	6				
EXPLAIN LOSSES					

EXPLAIN LOSSES
Some of this batch could possibly
be extended with Lot 11427

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED 6 NO DRUMS 15
SAMPLED BY 17 LUMP WGT 5167
RELEASED BY Pgi

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

SCREEN	RPM
MAX. TEMP.	F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1431
4100
17

0.00 *

3.48 +
0.12 -
3.80 +
0.12 -
3.82 +
0.12 -
3.44 +
0.12 -
3.57 +
0.12 -
3.73 +
0.12 -
3.56 +
0.12 -
3.71 +
0.12 -
3.57 +
0.12 -
3.55 +
0.12 -
3.60 +
0.12 -
3.66 +
0.12 -
3.59 +
0.12 -
3.48 +
0.12 -
2.91 +
0.12 -
51.67 *

YE 698 D
LOT 1427

6001