

Case: 48106-3

PLAINTIFF'S EXHIBIT

SWB-127

**Bell Laboratories**

600 Mountain Avenue  
Murray Hill, New Jersey 07974  
Phone (201) 582-3000

August 26, 1980

Mr. G. Lange  
New York Telephone Company  
1095 Avenue of the Americas  
New York, New York 10036

Dear Mr. Lange:

The two insulation samples have been analyzed for asbestos by Walter C. McCrone Associates, Inc. The technique used was polarized light microscopy with dispersion staining. Their results are reported in a letter dated August 11, 1980, with their reference #7931. Both samples had the same composition.

Sample: 1095 A of A 4th Fl CO (NE Corner) and  
Sample: 1095 A of A 4th Fl CO (SW Corner)

The above samples contained 80-85% chrysotile asbestos in a carbonate matrix.

If you have any questions about this analysis, please let me know.



Charles P. Lichtenwalner

MH-8691-CPL-sma

Ref: 1192

Copy to  
G. H. Collings, Jr., M.D. - NYT  
P. H. Stark

R. L. Beach - AT&T  
N. J. DeCapua  
J. M. Degen  
R. W. Stone, M.D.

THIS COPY FOR

W. J. Schreibeis  
G. M. Wilkening

CONFIDENTIAL

003624