PG 01 CODE YE-698-D PKG ____ 241 LOT

MAY -0-81-E 1497

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

YE-698-D (R) P. POS. 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPR

= INSTRUCTIONS = PRESSING = RECORD

VAT	241				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-18				STARTED	1234			
TIME	930				CAKES USED	50			
RELEASED BY	SY				WATER ON	5			
PRESS	2	91	92	93	HRS. WASHED	5½			
NO.OF CAKES	32	42	32	32	OHMS	7000			
PRESS WITH AGITATION					HRS. WASHED				
WASH TO 2000 OHMS 35-74 F WATER					OHMS				
TEST AFTER 2 HOURS					HRS. WASHED				
LOAD ON 4 CARS					OHMS				
					CAKE CONDITION				
					NO CARS LOADED	5			
					EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 12
LUMP WGT 3397

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1497
41
17

0.00 *

3.23 +
0.12 -
3.33 +
0.12 -
3.33 +
0.12 -
3.33 +
0.12 -
3.25 +
0.12 -
3.30 +
0.12 -
3.36 +
0.12 -
3.27 +
0.12 -
0.57 +
0.12 -
25.89 *

1497
41
305

0.00 *

25.89 +
3.01 +
0.12 -
3.07 +
0.12 -
2.36 +
0.12 -
33.97 *