CODE RJ-908 LOT 40033

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1,900	1	T	158	
1,890	1	T	315	
	STUMP	Lump 3755#		

TOTAL NET WT. 3,790 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
JN	5,5,87	

PRODUCT NAME = KROLOR YELLOW-LIGHT

CODE KY-908-D PKG ____

LOT MAY-0-81- 40033

EST'D WGT 1603 LBS

TOTAL EST'D WGT=~~6205~~ 3549 LBS (CRT ENTRY)

NON-BLEEDING
PROCESSES APPROVED BY
KY908D(F) FWP 01/27/81
ALTERNATE
TYPED BY WRT/JMW
MAKING NOTES _____

JOB NAME: 03KY908DPF

INSTRUCTIONS = PRESSING = RECORD

				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT	262			STARTED	4:30PM				
DATE	1-28-81 2-3-81			CAKES USED	48				
TIME				WATER ON	7:30PM				
RELEASED BY	A.G			HRS. WASHED	6				
PRESS	96	95		OHMS	2.0MΩ				
NO.OF CAKES	72	48		HRS. WASHED					
PRESS WITH 40 AGITATION				OHMS					
WASH TO 2000 OHMS - 135-145 F WATER				HRS. WASHED					
TEST AFTER 3 HOURS				OHMS					
LOAD ON 16 6 CARS				CAKE CONDITION					
				NO CARS LOADED	8				
				EXPLAIN LOSSES					

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

Color appears dry.

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 13
LUMP WGT 3759

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

= GRINDING =

MILL 939 HSP 1/8"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050096270

KY-908

40033
41
305

	0.00	*
	3.21	+
	0.12	-
	3.24	+
	0.12	-
	3.18	+
	0.12	-
	3.35	+
1	0.12	-
	3.39	+
	0.12	-
	3.19	+
	0.12	-
	3.33	+
	0.12	-
13	3.23	+
	0.12	-
	2.99	+
	0.12	-
	3.13	+
	0.12	-
	3.23	+
	0.12	-
	2.93	+
1	0.12	-
	0.75	+
	0.12	-
	37.59	*

DUP050096271