

01 CODE YE-698-D PKG

LOT MAY -0-81-E1104

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS				= PRESSING =	RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES	
1242	5-1-81	3:25 PM	JN	2	92	93	54	54	54	54	54	54	54	54	54	54	54	54	54	54	54	54	54

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =
(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 17
LUMP WGT 5928

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

= GRINDING =
RPM SCREEN RPM
MAX. TEMP. F

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1104
41
56

0.00 *

12
3.33 +
0.12 -
3.39 +
0.12 -
3.25 +
0.12 -
3.50 +
0.12 -
3.51 +
0.12 -
3.89 +
0.12 -
3.46 +
0.12 -
3.41 +
0.12 -
3.65 +
0.12 -
3.22 +
0.12 -
3.35 +
0.12 -
3.11 +
0.12 -
39.63 *

1104
41
305

0.00 *

7
39.63 +
3.21 +
0.12 -
3.28 +
0.12 -
3.01 +
0.12 -
3.41 +
0.12 -
2.95 +
0.12 -
3.15 +
0.12 -
1.48 +
0.12 -
59.28 *