

VISCOSITY WORK SHEET

Item 3069 P.T.No. _____ Date 10 / 55
 Worker Agnew Polymer Lucite Solvent EAC
 For Comparison Charge 1290 Temperature 25°C
 Viscometer No. C Efflux Time 204.1 Weight: Gross 5.1393
 Viscometer No. M Efflux Time 155.1 Tare 5.0643
 Viscometer No. L Efflux Time 180.6 Net 1250

B
 10
 Visc.

167.4
 211.8

Sample Flask No. _____ Solution Efflux Times _____

Rel. Inh. visc.
 Visc. or M.W.

4819-153-W	LSK	10	254.4; 255.0; 254.8	1.203	81,500 ✓
"	AP	C	245.7; 245.7; 245.6	1.203	81,500 ✓
4819-153-X	NAG	M	221.3; 221.8; 221.4	1.209	84,500 ✓
"	J-5	L	218.0; 217.5; 217.6	1.207	83,500 ✓
4819-153-Y	L-1	B	205.0; 203.0; 203.2	1.213	86,500 ✓
"	H-20	10	257.5; 257.5; 257.5	1.215	87,500 ✓
4819-153-Z	Agg	C	249.4; 248.7; 248.9	1.219	89,500 ✓
"	EO	M	224.2; 223.9; 224.0	1.221	90,500 ✓
4819-153-AA	7	L	225.0; 224.7; 221.2	1.223	92,000 ✓
"	12	B	205.0; 204.9; 204.8	1.222	91,000 ✓
133V	93	10	253.1; 253.1	1.196	77,000 ✓
"	K2	B	199.8; 199.8	1.194	76,000 ✓
4847-106	34	C	250.0; 249.9; 249.8	1.224	92,500 ✓
"	K-4	M	224.4; 224.6; 224.7	1.22	94,000 ✓
4847-107	14	L	221.2; 221.3; 221.4	1.225	93,000 ✓
"	24	B	205.3; 205.5; 205.3	1.226	93,500 ✓

PC-1

N38820