

UNION
CARBIDE

PLAINTIFF'S
EXHIBIT

KM-199

Calidria

***Resin-
Grade
144
Asbestos***

- Effective, low-cost thickening agent and thixotrope for epoxy resin systems
- Imparts excellent viscosity control to resin systems (coatings, adhesives, sealants, caulks, mastics)

KMX 02079

The logo for Calidria, featuring the word "Calidria" in a stylized, italicized serif font, enclosed within a white, curved, ribbon-like shape that tapers at both ends.

Resin-Grade 144

The word "Asbestos" in a large, bold, italicized sans-serif font. The letter "A" is significantly larger than the other letters and is partially overlapped by a thick, black, diagonal bar that extends from the left edge of the page towards the top right.

... a highly purified fiber product that is an effective, low-cost thickening agent and thixotrope for epoxy resin systems. By means of a special refining technique developed by UNION CARBIDE, CALIDRIA Resin-Grade 144 Asbestos is made completely grit-free and non-abrasive—this latter characteristic makes it especially valuable in spray application.

Other desirable features of CALIDRIA Resin-Grade 144 Asbestos include:

- Disperses easily in liquid resin or hardener with a "Cowles" Dissolver or similar mixers
- Overmixing will not destroy the thixotropy of the resin-asbestos mixture
- Epoxy systems containing CALIDRIA Resin-Grade 144 Asbestos have excellent aging characteristics
- Reduced dust
- Unlike other thixotropes, it is effective with amine hardeners
- CALIDRIA Resin-Grade 144 Asbestos is substantially lower in cost than commonly used refined silicas or modified clays
- No amine salts are necessary for viscosity build-up or thixotropic stabilization (with the exception of the low-viscosity, cycloaliphatic epoxides)

Typical physical properties

Specific Gravity.....	2.45
Moisture Content, % by wt.....	2.0, maximum
Surface Area, sq. meters per gram.....	60, appr.
Reflectance, G. E. Brightness.....	72-76
Nature of Surface Charge.....	Electropositive (cationic)
pH in Water.....	9.5
Bulking Value, gallons per 100 lb.....	4.8
Oil Absorption (DOP), pounds per 100 lb.....	120-140
Refractive Index, $n_D 25^\circ \text{C}$	1.54-1.56
Wet Bulk Density in Water, ml. as received, 20 g. per liter; 3-hr. settling.....	700
after dispersion, 2 g. per liter; 1-hr. settling.....	900-1,000
Dry Bulk Density, lb. per cubic foot.....	4
Shipping Density, lb. per cubic foot.....	12-14
Standard Package Weight, lb.....	35
% Magnetite.....	0.6
Screen Size, Typical; % plus 325 mesh.....	Nil
Fiber Diameter, microns.....	0.025
Length/Diameter, microns.....	200 avg. (1000 maximum)

IMPORTANT: This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation, and verification.

BAKELITE, CALIDRIA and UNION CARBIDE are trade marks of Union Carbide Corporation, U. S. A.

© 1967, 1968, 1969 by Union Carbide Corporation.

Typical applications

Figure 1 THICKENING EFFICIENCY IN LIQUID EPOXY RESINS





Figure 1 illustrates the effective, low-cost thickening and viscosity control properties of CALIDRIA Resin-Grade 144 Asbestos in epoxy resin systems. It compares relative differences in viscosity of BAKELITE Epoxy Resin ERL-2774 solutions containing equivalent concentrations of CALIDRIA R-G 144 Asbestos, micro-crystalline silicate, and pyrogenic silica.

Figure 2 illustrates the ability of CALIDRIA R-G 144 Asbestos to control viscosity in two different solvent-epoxy systems used in many epoxy coatings and paints.

Figure 2 VISCOSITY CHARACTERISTICS OF CALIDRIA R-G 144 IN BAKELITE® EPOXY SOLUTIONS



Resin and amine hardener evaluation

METHOD OF INCORPORATING THE THIXOTROPE:

In preparing the test samples used in determining data for Tables 1, 2 and 3, the thixotrope—CALIDRIA Resin-Grade 144 Asbestos—was added to the liquid resin or hardener at 25°C. and dispersed in a "Cowles" Dissolver at 2400 rpm. for 5 minutes.

VISCOSITY MEASUREMENTS:

Viscosities of the prepared test samples were measured on a Brookfield Model RVF Viscometer at 2 and 20 rpm.

Table 1 shows performance data of bisphenol based resins, BAKELITE ERL-2774 and ERL-2795, with up to 4 PHR. of CALIDRIA Resin-Grade 144 Asbestos. Vertical draw-down was excellent, and even higher asbestos loading should result in even higher vertical draw-down.

Table 1 THICKENING OF BISPHENOL-BASED RESINS
WITH CALIDRIA RESIN-GRADE 144 ASBESTOS

Ingredient	Parts by Weight											
	100			100			100			100		
	1			2			3			4		
	RPM.		Thixotropic Index (T. I.) (a)	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)
Brookfield RVF Viscosity, cps. X 10 ⁻¹	2	20		2	20		2	20		2	20	
24 hours	34	22	1.5	137	39	3.5	250	53	4.7	464	87	5.3
7 days	32	20	1.6	132	36	3.6	244	54	4.5	430	76	5.7
30 days	(b)	(b)	(b)	(b)	(b)	(b)	(b)	(b)	(b)	480	94	5.1
Vertical Drawdown, mil (c)												
Room Temperature	(b)			(b)			(b)			125		
45 days	(b)			(b)			(b)			125		

Ingredient	Parts by Weight											
	100			100			100			100		
	1			2			3			4		
	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)
Brookfield RVF Viscosity, cps. X 10 ⁻¹	2	20		2	20		2	20		2	20	
24 hours	18	3.8	4.7	38	6.3	6.0	70	11	6.4	91	13	6.9
7 days	16	3.7	4.3	35	6.8	5.1	68	12	5.5	122	22	5.5
30 days	(b)	(b)	(b)	(b)	(b)	(b)	(b)	(b)	(b)	125	25	5.0
Vertical Drawdown, mil (c)												
Room Temperature	(b)			(b)			(b)			80		
45 days	(b)			(b)			(b)			70		

(a) Thixotropic Index (T. I.) = $\frac{\text{viscosity at 2 rpm.}}{\text{viscosity at 20 rpm.}}$

(b) Not run.

(c) Vertical Drawdown: A 2-inch wide drawdown was made on a horizontal sandblasted steel panel. The panel was immediately raised to a vertical position and any sag noted. If no sag occurred in 10 minutes, the procedure was repeated and the thickness increased until sagging occurred.

Table 2 presents data that show the effectiveness of CALIDRIA Resin-Grade 144 Asbestos as a thickener of several types of BAKELITE Amine Hardeners. Generally, other thickeners are not effective with amine hardeners.

Table 2 THICKENING OF AMINE HARDENERS
WITH CALIDRIA RESIN-GRADE 144 ASBESTOS

Formulation	Parts by Wt. BAKELITE ZZL-0814.....100 CALIDRIA Resin-Grade 144 Asbestos.....4			Parts by Wt. BAKELITE ZZL-0820.....100 CALIDRIA Resin-Grade 144 Asbestos.....4			Parts by Wt. BAKELITE ZZL-0854.....100 CALIDRIA Resin-Grade 144 Asbestos.....4		
	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)	RPM.		Thixotropic Index (T. I.)
	2	20		2	20		2	20	
Brookfield RVF Viscosity, cps. X 10 ⁻³									
24 hours	187	36	5.3	67	32	2.1	102	23	4.5
7 days	172	34	5.1	66	32	2.1	104	23	4.6
30 days	177	34	5.2	67	35	1.9	104	24	4.4
Vertical Drawdown	Mil			Mil			Mil		
Room Temperature (R. T.)	70			40			40		
50°C.	20			—			—		
80°C.	—			40			40		
30 days at R. T.	70			40			40		
30 days at 80°C.	—			40			40		

Table 3 shows the thickening of a low-viscosity, cycloaliphatic epoxide, BAKELITE ERL-4221, with CALIDRIA Resin-Grade 144 Asbestos and "Armac" C, a long chain aliphatic amine salt. BAKELITE ERL-4221 is the exception that requires an amine salt to be used with CALIDRIA Resin-Grade 144 Asbestos for viscosity build-up or thixotropic stabilization.

Table 3 THICKENING OF A
LOW-VISCOSITY,
CYCLOALIPHATIC EPOXIDE WITH
CALIDRIA RESIN-GRADE 144
ASBESTOS AND "Armac" C

Ingredient		Parts by Wt.	
BAKELITE ERL-4221.....		100	
CALIDRIA Resin-Grade 144 Asbestos.....		7	
"Armac" C.....		5	
Brookfield RVF Viscosity, cps. X 10 ⁻³	RPM.		Thixotropic Index (T.I.)
	2	20	
Initial	262	42	6.3
8 Weeks at 25°C.	268	36	7.4
7 Weeks at 40°C.	243	38	6.4

Systems evaluation

BAKELITE ERL-2774/ZZL-0814

With a CALIDRIA Resin-Grade 144 Asbestos loading of 4 per cent on both resin and hardener, it was possible to hold a 70-mil thickness at room temperature. Higher loadings on the amine should result in much higher vertical drawdown.

BAKELITE ERL-2774/ZZL-0820

A 4-per cent loading of CALIDRIA Resin-Grade 144 Asbestos resulted in a 40-mil thickness that did not sag within 40 minutes at 80°C. The system was gelled at that time.

BAKELITE ERL-2774/ZZL-0854

With a 4-per cent loading of CALIDRIA Resin-Grade 144 Asbestos, it was possible to hold a 40-mil thickness at 80°C. until gelled (65 minutes).



THE DISCOVERY COMPANY

UNION CARBIDE CORPORATION

ASBESTOS

270 PARK AVENUE, NEW YORK, N. Y. 10017

Sales Offices

United States

ATLANTA, GEORGIA 30329	17 Executive Park Dr.	404-633-6161
BALTIMORE, MARYLAND 21207	Beltway Bldg., 6707 Whitestone Rd.	301-944-8211
BOSTON, MASSACHUSETTS 02194	300 First Ave., Needham Hgts.	617-444-5400
BUFFALO, NEW YORK 14225	3343 Harlem Rd.	716-837-6450
CHARLOTTE, NORTH CAROLINA 28210	6230 Fairview Rd.	704-364-1400
CHICAGO, ILLINOIS 60606	120 South Riverside Plaza	312-822-7000
CINCINNATI, OHIO 45227	West Street and Madisonville Rd.	513-272-0206
CLEVELAND, OHIO 44114	1300 Lakeside Ave., N.E.	216-621-4202
CLIFTON, NEW JERSEY 07012	935 Allwood Rd.	201-778-2900
DALLAS, TEXAS 75207	2710 Stemmons Freeway	214-631-0010
DETROIT, MICHIGAN 48221	10421 West Seven Mile Rd.	313-341-3131
HOUSTON, TEXAS 77027	3839 West Alabama Ave.	713-621-1000
INDIANAPOLIS, INDIANA 46220	720 Broad Ripple Ave.	317-255-3181
KANSAS CITY (ST. LOUIS SALES OFFICE)		913-362-2200
LOS ANGELES, CALIFORNIA 90058	2770 Leonis Blvd.	213-583-3061
MEMPHIS (ATLANTA, GA. SALES OFFICE)		901-396-5375
MINNEAPOLIS, MINNESOTA 55416	3033 Excelsior Blvd.	612-927-4221
MOORESTOWN, NEW JERSEY 08057	Route 38 and Pleasant Valley Rd.	609-235-6200
NEW YORK, NEW YORK 10017	270 Park Ave.	212-551-4641
PHILADELPHIA (MOORESTOWN, NEW JERSEY SALES OFFICE)		215-923-3200
PITTSBURGH, PENNSYLVANIA 15220	P'kway Center, 875 Greentree Rd.	412-922-5700
ST. LOUIS, MISSOURI 63105	10 South Brentwood Blvd.	314-726-0324
SAN FRANCISCO, CALIFORNIA 94106	22 Battery St.	415-982-1360
SEATTLE, WASHINGTON 98118	4726 Rainier Ave., South	206-723-8660



CALIDRIA Resin-Grade 144

Asbestos



PRICE LIST

Effective: January 2, 1971
Supersedes: January 31, 1970

RG-144

... a highly refined fiber used as a low-cost, efficient thixotrope and viscosity control agent in epoxy, phenolic, and similar resin compounds used in mastics, adhesives, sealants, caulks, and coatings.

NET PRICES - CENTS PER LB. - F.O.B. SHIPPING POINT					
SHIPPING POINTS	ORDERING QUANTITY Quantities more than 1,400 lb. sold only in full-pallet multiples.				
	Carload, 72,800 lb.	23,800 lb. or more	8,400 lb. to 22,400 lb.	1,400 lb. to 7,000 lb.	175 lb. to 1,365 lb.
	52 pallets	17 or more pallets	6 to 16 pallets	1 to 5 pallets	Less than 1 pallet
King City, Calif. (plant)	12.0	12.0	15.0	19.0	25.0
Torrance, Calif.	—	14.0	17.0	21.0	27.0
Atlanta, Ga. Cleveland, O. Columbus, O. Detroit, Mich. Hammond, Ind. St. Louis, Mo. Dallas, Tex. Houston, Tex.	—	15.0	18.0	22.0	29.0
Metuchen, N.J.	—	16.0	19.0	23.0	31.0

PACKAGING INFORMATION	One Package	35 lb.
	One Pallet	1,400 lb.
	50-ft. Carload	72,800 lb. (52 pallets)
	40-ft. Truckload	23,800 lb. (17 pallets)

KMX 02080

• Packages are sealed with polythylene overwrap.

COMBINED SHIPMENTS — Shipments of one or more pallets of any "Calidria" asbestos product may be combined with one or more pallets of any other "Calidria" product for total quantity price. Less than pallet quantities may not be combined for total quantity price.

IMPORTANT — Payment terms: Net 10th proximo. Minimum order: 175 lb. Prices apply within continental U.S.A. Union Carbide reserves the right to adjust customer's orders to comply with the standard ordering quantities specified above.

UNION CARBIDE CORPORATION • MINING AND METALS DIVISION • 270 PARK AVENUE, NEW YORK, N.Y. 10017

This paper contains "Calidria" asbestos T-135, an efficient, low-cost opacifier. It is 80-lb. Fairmount offset produced by Tileston & Hollingsworth Co., a subsidiary of Diamond International Corporation.

